

**Section 03 33 00 Architectural Concrete  
Technical Data Sheet**



**Ameripolish® X-Link™ WB Surface Sealer**

**PROFESSIONAL USE ONLY**



**X-Link™ WB Surface Sealer  
HIGH STRENGTH CROSS LINKING SEALER**

**INTERIOR/EXTERIOR**

PROTECT AND BEAUTIFY DECORATIVE CONCRETE  
SATIN FINISH & NON-YELLOWING  
ADDED UV & MILDEW PROTECTION  
LONG LASTING WITH EXCELLENT DURABILITY  
BREATHABLE & DRIES FAST  
OIL & CHEMICAL RESISTANT

**◆ PRODUCT DESCRIPTION**

Ameripolish® X-Link™ WB Surface Sealer is a sprayable, low VOC, fast drying water-based sealer designed to protect and beautify decorative concrete. X-Link™ WB Surface Sealer may be used to seal concrete with no color or with other compatible color products. X-Link™ is water and chemical resistant.

**◆ FEATURES**

- Exterior and interior applications
- Penetrating and durable
- Satin Finish
- Non-Yellowing
- UV Resistant
- Fast application, 1hr drying
- Fast curing, 12 hours for foot traffic, 24 hours for heavy traffic
- Water-based
- Breathable
- Helps prevent black marks from chewing gum
- Can be applied to most cementitious surfaces, other unglazed stone, and masonry surfaces

**◆ PRODUCT SPECIFICATIONS**

Application:	On Broom finish you can just spray on, and on smooth surfaces you can use an Ameripolish® Microfiber Pad.
Appearance:	Milky liquid
VOC:	Compliant (<5g/l)
Shelf Life:	1 Year
Solvent:	Water Based

**◆ USES**

Ameripolish® X-Link™ WB Surface Sealer can be used on interior or exterior masonry and concrete-type surfaces. Use on colored or uncolored, stamped or exposed aggregate concrete, porous brick, natural and manufactured stone, stucco, slate, unglazed tile and flagstone.

**◆ PREPARATION**

**WARNING:** People, property, vehicles, animals, plants, and all surfaces not intended to be sealed should be protected from the product, splash, over-spray, and wind drift, using polyethylene sheeting or other proven

protective material.  
NEW CONCRETE MUST CURE FOR AT LEAST 28 DAYS BEFORE APPLICATION. For best results, perform a moisture content test on both newly-poured and existing slabs. Slabs with a moisture content 5 lbs per 1000 sf or less show best performance (ASTM F1869 calcium chloride test). High moisture levels may affect performance of sealer. Do not apply if concrete is frozen, dirty or has standing water. Hydrostatic pressure may affect sealer performance. Surface to be sealed must be completely clean. Remove efflorescence, oil, dirt, wax, paints, sealers, and curing compounds; pressure wash and/or power scrub if necessary. Ameripolish® Strip & Clean™ is highly recommended to clean the surface.

**◆ COVERAGE**

X-Link WB Surface Sealer™ will cover 400-600 square feet per gallon depending upon porosity of concrete that is broom finished or concrete that is not mechanically finished. X-Link™ will cover 400-600 square feet per gallon when applied to mechanically finished concrete.

**◆ APPLICATION**

Testing: Prior to starting project, apply X-Link™ to sample area of each type of concrete to be treated, using

**◆ VOC COMPLIANCE**

In addition, Ameripolish® X-Link™ Sealer offers VOC compliance with low VOC at <5g/L and is also compliant with national, state and district regulations:  
US Environmental Protection Agency  
California Air Resources Board SCM Districts\*  
South Coast Air Quality Management District\*  
Maricopa County, AZ  
Northeast Ozone Transport Commission  
\*Before application, verify product conformance with local and state codes.

**Ameripolish® X-Link™ WB Surface Sealer**

application procedures proposed for project. Confirm that concrete is receptive to sealer.  
 Project Conditions: Ambient temperature during application should be 55°F-80°F (12.8°C -26.7°C). Do not apply on rainy, foggy, or extremely humid days. Excess moisture may prevent sealer from drying properly.  
 Equipment: Apply X-Link™ using a low pressure sprayer fitted with a conical mist tip Green #4. An Ameripolish® Microfiber pad or similar microfiber floor finish applicator pad may be used.  
 Application: Apply 1 coat.

**◆ SAFETY PRECAUTIONS**

**WARNING** – Before using or handling this material, read the Material Safety Data Sheet and Warranty. **EYE, SKIN AND GASTRO-INTESTINAL TRACT AND RESPIRATORY TRACT IRRITANT.** Avoid contact with eyes, skin and clothing. Avoid breathing vapors or mists generated by this product. Use appropriate eye protection, and chemical-resistant gloves. Material is not flammable, but if exposed to fire material may produce irritating vapors and toxic gases (e.g., carbon dioxides and peroxides). **KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY.**

**◆ NEXT STEPS**

Foot traffic may be allowed on sealed surface after 12 hours. For heavy traffic, allow 24 hours curing.

**◆ MAINTENANCE**

Sealed surface should be inspected periodically for areas of thin or traffic worn sealer, and sealer reapplied as needed. Normal traffic may require reapplication of X-Link™ annually. Use Ameripolish® MultiPurpose Rejuvenating Cleaner® for long lasting protection.

**◆ STORAGE**

- Store dry and upright at 40-105F° (4 - 41C°)
- Keep product from freezing
- Keep out of reach of children
- Seal container after use.

**◆ WARRANTY**

The information contained herein is believed to be reliable. This information is based on laboratory testing and results. Because of variations in methods, conditions and equipment, each user must test this product to make a judgment of performance. Applicator is responsible for testing material for effectiveness and

performance. Manufacturer obligation is limited to the refund of purchase price or replacement of material if proven to be defective. Claims must be made in writing and received within one year from date of product sale to original buyer. Sole remedy shall be replacement of product proven defective.

**◆ FIRST AID**

**Ingestion: CALL PHYSICIAN OR POISON CONTROL CENTER FOR MOST CURRENT INFORMATION.** If professional advice is not available, **DO NOT INDUCE VOMITING.** If victim is convulsing, maintain an open airway and obtain immediate medical attention. **Eye Contact:** Rinse eyes under gently running water. Use sufficient force to open eyelids and then “roll” eyes while flushing. Flush for 15 minutes minimum. Seek medical attention if any adverse effect persists after rinsing. **Skin Contact:** If adverse skin effects occur, discontinue use and flush contaminated area. Seek medical attention if adverse effect occurs after flushing. **Inhalation:** Remove victim to fresh air. If necessary, use artificial respiration to support vital functions. If adverse effect continues after removal to fresh air seek medical attention.

Product Name – Ameripolish® X-Link™ WB Surface Sealer			Product Name – Ameripolish® X-Link™ WB Surface Sealer		
Product #	Shipping Wt.	Container(s) RTU: Ready To Use	Product #	Volume (RTU)	Coverage Sq. ft.
XS-1	10 lbs.	RTU – 1 Gal	XS-1	1 Gal.	300 Min. – 500 Max.
XS-5	50 lbs.	RTU – 5 Gal	XS-5	5 Gal.	1,500 Min. – 2,500 Max
XS-30	300 lbs.	RTU – 30 Gal	XS-30	30 Gal.	9,000 Min. – 15,000 Max
XS-55	550 lbs.	RTU – 55 Gal	XS-55	55 Gal.	16,500 Min. – 27,500 Max
XS-250	2500 lbs.	RTU – 250 Gal	XS-250	250 Gal.	75,000 Min. – 125,000 Max



Warning:  
 Causes skin irritation  
 Causes serious eye irritation



AmeriPolish, Inc. 120 Commercial Ave., Lowell, AR 72745 USA  
 Toll Free: 1.800.592.9320 Office: +1 479.725.0033 Fax: +1 479.725.0031  
 info@ameripolish.com ◆ www.ameripolish.com