



ARDEX FDX™

Full Depth Extended Repair Mortar

Concrete Repair Mortar with Corrosion Inhibitor

**Portland cement-based structural repair mortar with
integral corrosion inhibitor**

Pre-measured aggregate increases productivity

Mix with water only

Easy to apply – formable, pourable and pumpable

Installs from 1 1/2" to 8"

Suitable for overlays and full depth repairs

Freeze-thaw resistant

**Suitable for commercial, institutional and multi-unit
residential applications**

Use for exterior and interior concrete repair

Apply coatings in as little as 72 hours after application

ARDEX Engineered Cements
400 Ardex Park Drive
Aliquippa, PA 15001 USA
Tel: 724-203-5000
Toll Free: 888-512-7339
Fax: 724-203-5001
www.ardex.com

ARDEX FDX™ Full Depth Extended Repair Mortar

Concrete Repair Mortar with Corrosion Inhibitor

Description and Usage

ARDEX FDX™ is a formable, pourable, pumpable, Portland cement-based structural repair mortar for horizontal, vertical and overhead applications for exterior and interior concrete above, on or below grade. ARDEX FDX contains pre-blended aggregate for precise jobsite control. It is used at depths ranging from 1 1/2" to 8", has a corrosion inhibitor built-in to protect reinforcing steel, is easy to apply, and readily bonds to concrete. The resulting patch has low shrinkage and resists delamination. Typical applications include balconies, plaza decks, columns, walls and parking decks.

Substrate Preparation

Prior to proceeding with any repair, please refer to the International Concrete Repair Institute's ICRI 03730 Guide for Surface Preparation for the Repair of Deteriorated Concrete Resulting from Reinforcing Steel Corrosion; ICRI 03732 Guideline for Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, and Polymer Overlays; and the American Concrete Institute's ACI 546R-04 Concrete Repair Guide for general guidelines for concrete repair.

The repair area must be saw cut in a basic rectangular shape to at least 1 1/2" in depth. The cuts should be made at approximately a 90° angle, and should be slightly keyed. Chip out the concrete inside the cuts to a minimum depth of 1 1/2" until the area is squared or boxed in shape.

All substrates must be solid, thoroughly clean and free of oil, wax, grease, asphalt, existing patching materials, curing and sealing compounds, and any contaminant that might act as a bond breaker. Over watered, frozen or otherwise weak concrete surfaces must also be cleaned down to sound, solid concrete by mechanical methods such as scarifying or similar in accordance with ICRI 03732 to create an exposed aggregate surface with a minimum surface profile of approximately 1/16" (1.6 mm). Acid etching, solvents, sweeping compounds and sanding are not acceptable means of preparing the substrate.

For cases with exposed reinforcing steel, mechanically clean the steel to remove all rust and any other contaminants in accordance with ICRI 03730. Prime the steel with ARDEX BONDING & ANTI-CORROSION AGENT™ prior to proceeding with the repair. For further details, please refer to the ARDEX Technical Brochure.

Cracks and Joints

Saw cuts and dormant cracks greater than 1/16" (1.6 mm) should be filled with an ARDEX ARDIFIX™ joint filler or similar prior to installing ARDEX FDX. The joint filler should be installed in strict accordance with the instructions provided by the filler manufacturer. The filling of dormant cracks and joints as described is recommended to help prevent telegraphing. However, should movement occur, cracks and joints will reappear.

All moving joints and cracks must be carried up through the ARDEX FDX by installing a flexible sealing compound specifically designed for use over moving joints, such as ARDEX ARDISEAL™ RAPID PLUS joint filler or similar.

Recommended Tools

A 1/2" to 3/4" (12 to 19 mm) low speed heavy-duty mixing drill, heavy gauge square box (butterfly) mixing paddle, mixing buckets, measuring container, margin trowel, wood or magnesium float, steel trowel and wood planking for forming. Also suitable for mixing in forced action mortar mixers.

Priming

If ARDEX BONDING & ANTI-CORROSION AGENT is specified as a primer, follow the application instructions in the ARDEX Technical Brochure.

If this primer is not used, dampen the concrete to be repaired until it is thoroughly saturated. Do not leave any bare spots. Brush or vacuum off puddles and excess liquid. The goal is to saturate the pores of the concrete while leaving the surface free of water (SSD, Saturated Surface Dry). Alternatively, ARDEX P 71™ PRIMER can be used in accordance with the ARDEX Technical Brochure. Do not allow the concrete or ARDEX P 71 to dry before installing the ARDEX FDX. Installing the mortar over a surface that is too dry can result in cracking and bond failure.

Mixing and Application

Pre-dampen the inside of a pail or the inside of a clean mortar mixer, and remove any excess water. Pour in 6 1/2 pints (3.08 L) of clean water, and then slowly add one-third of an 80 lb (36.4 kg) bag of ARDEX FDX. Once this is blended in, add the next third and so on until all of the material is added. If mixing in a pail, mix with a low speed drill and mixing paddle for approximately 3 minutes to a uniform,

lump-free consistency. If using a mortar mixer, mix for approximately 4 minutes until uniform and lump free. For both mixing methods, avoid over mixing, which may entrap air. If additional water is required, you may add up to 8 oz (0.24 L) of additional mix water per bag. **Do not overwater.**

ARDEX FDX is easily applied to any prepared concrete surface using standard concrete practices. Once mixed, the pot life and working time are 20 to 40 minutes, depending on surface and ambient temperatures. All mixed material must be placed within this time. Once placed, allow the material to take an initial set before finishing. Cool ambient and surface temperatures will slow the setting time, while high temperatures will accelerate it.

When overlaying, work a scrub coat of the mixed material into the primed or SSD concrete substrate, applying enough pressure to ensure good mortar-to-concrete contact. Apply the repair mortar while the scrub coat is still wet. If the scrub coat is allowed to dry, it must be mechanically removed and reapplied before applying the mortar. Once the mortar is applied, consolidate to remove any air pockets.

When pouring into closed forms, the repairs can be vibrated to ensure full contact and to establish bond with the substrate, as well as to ensure proper consolidation. Avoid over-vibration.

Steel trowel the mortar to the desired finish once it takes its initial set. Applications when temperatures are above 85°F (29°C) should follow the appropriate Warm Weather Installation Guidelines available from the ARDEX Technical Service Department.

Thickness of Installation

ARDEX FDX can be installed from a minimum of 1 1/2" up to 8" neat (38 mm to 20.3 cm).

Curing

Direct sunlight or wind may cause unwanted rapid surface drying. Keep the surface of the installation damp for 48 hours (light water fogging, curing blanket or curing compound). Do not allow water to puddle. Do not use solvent-borne curing compounds. **Note:** if the surface is to receive a top coat or other type of finish, use moist curing methods only.

Surface Finish and Sealing

Once the repair has cured for a minimum of 72 hours it can be coated, topped or sealed as specified. Cold and damp conditions may extend this time. To view the toppings, dressing and sealers available from ARDEX, please visit www.ardex.com.

Notes

The working time and pot life of ARDEX FDX are approximately 20 to 40 minutes at 70°F (21°C). Pot life and working time will vary with ambient temperatures.

ARDEX FDX is intended for repairing and resurfacing exterior or interior concrete in institutional, commercial and multi-unit residential areas.

Always install an adequate number of properly located test areas, including the finishes, to determine the suitability of the products for the intended use. As finishes vary, always contact and rely upon the finish manufacturer for specific directives such as maximum allowable moisture content, sealer selection and intended end use of the product.

Never mix with cement or additives. Observe the basic rules of concrete work. Do not install below 50°F (10°C) surface and air temperatures. These temperatures must also be maintained during and for 48 hours after the installation of ARDEX FDX. Install quickly if the substrate is warm, and follow warm weather instructions available from the ARDEX Technical Service Department.

Precautions

ARDEX FDX contains Portland cement and silica. Avoid eye and skin contact. Mix in a well-ventilated area and avoid breathing powder or dust. **KEEP OUT OF REACH OF CHILDREN.** Carefully read and follow all cautions and warnings on the product label. For complete safety information, please refer to the Material Safety Data Sheet or visit our website at www.ardex.com.

Technical Data According to ARDEX Quality Standards

All data based on recommended mix ratio at 70°F (21°C)
Physical properties are typical values and not specifications

Mixing Ratio: 6 1/2 pints (3.08 L) of water
per 80 lb (36.4 kg) bag

Yield: 0.62 cu. ft. per 80 lb bag
(0.0175 m³ per 36.4 kg bag)
5 sq. ft. per 80 lb bag at 1 1/2"
(0.46 m² per 36.4 kg bag at
38.1 mm)

EXTENDED

Compressive Strength: 1 day 3200
(psi) ASTM C39 7 days 4800
28 days 6000

Flexural Strength (psi): 7 days 700
ASTM C293 28 days 750

Splitting Tensile: 7 days 400
Strength (psi) 28 days 600
ASTM C496

Modulus of Elasticity: 28 days 3.9 x 10⁶
(psi) ASTM C469

Length Change %: 28 days < 0.030
ASTM C157

Direct Tensile Bond: 28 days 210
(psi) ASTM D 4541

Pot Life/: 20 to 40 minutes
Working Time

Coat or Seal: Min. 72 hours

Color: Gray

Packaging: 80 lb (36.4 kg) net weight bags

Storage: Store in a cool dry area. Do not
leave bags exposed to direct
sunlight. Keep from freezing.

Shelf Life: One year if unopened

Warranty: ARDEX Engineered Cements
Standard Limited Warranty Applies

© 2011 ARDEX, L.P. All rights reserved.

ATX103 (02/11)

ARDEX Engineered Cements
400 Ardex Park Drive
Aliquippa, PA 15001 USA
Tel: 724-203-5000
Toll Free: 888-512-7339
Fax: 724-203-5001
www.ardex.com