Dynamic Coatings Inc. | (877) 225-2549 | www.dciflooring.com



95 Goodwin Street East Hartford, CT 06108

Tel: 800-253-3539 • Fax: 860-528-2802 • www.dur-a-flex.com • contact_us@dur-a-flex.com

DUR-A-WALL / DUR-A-WALL FGR

DESCRIPTION

DUR-A-WALL and DUR-A-WALL FGR Epoxy Wall Systems are pigmented, two component, low odor, 100% thermosetting epoxy formulations. DUR-A-WALL FGR (fiberglass reinforced) uses the same epoxy system as our DUR-A-WALL system but incorporates a fiberglass mat designed especially for drywall applications. DUR-A-WALL is ideally suited for application on concrete, wood, drywall, cement board or block. This coating is extremely durable, sanitary and easy to clean. DUR-A-WALL FGR is designed for use on drywall only. Two coats of a urethane topcoat with a high gloss or satin finish are recommended to provide protection against very aggressive solvents, acids and alcohols. Urethane topcoats are stain resistant and provide a high degree of abrasion resistance.

BENEFITS

- Stain Resistant
- Easy to Clean
- Seamless
- Durable
- Sanitary
- Easy

Maintenance

LIMITATIONS

This product is best suited for application in temperatures between 55°F and 95°F. Substrate must be clean, sound and dry. Failure to apply the recommended urethane topcoat will result in the systems' inability to maintain chemical and abrasion resistance and UV stability. DUR-A-WALL FGR should be applied on drywall only.

TYPICAL USES

- Laboratories
- Walk-In Coolers
- Pharmaceutical Plants
- Food Processing Plants
- Commercial Kitchens
- Clean Rooms
- Car Wash Bays
- Locker Rooms

- Hospitals
- Laundries
- Kennels
- Bottling Plants
- Garages
- Warehouses
- Schools

COLORS

DUR-A-WALL and DUR-A-WALL FGR is available clear or in 15 standard colors. Please refer to the Standard Color Chart on our website. Custom colors are available upon request.

PACKAGING

DUR-A-WALL and DUR-A-WALL FGR Epoxy Wall Systems are packaged in 1-gallon cans, 5-gallon pails and 50-gallon drums. The PGM semi-rigid fiberglass mat is available in 36" width at 540 Sq Ft per roll. Shelf life is one year in the original unopened containers.

SURFACE PREPARATION

This product requires preparation in order to perform as expected. Substrate must be clean, sound and dry. Please refer to the master Surface Preparation Guide on our website for more information.

APPLICATION METHOD /SPREAD RATES

DUR-A-GARD pigmented epoxy is used throughout the DUR-A-WALL and DUR-A-WALL FGR systems for base, grout and seal coats. Typically, DUR-A-GARD epoxy is applied with a 3/8" nap roller at approximately 200 Sq Ft per gallon to yield an even 8 mils wet film thickness with no runs. Coverage will vary depending on porosity and texture of substrate.

GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please refer to the master Specifier's Guide for complete three part guide specs in multiple formats.

CHEMICAL RESISTANCE

This product is resistant to most common chemicals. Please refer to the master Chemical Resistance Chart for actual resistance to specific chemicals/reagents.

DUR-A-WALL/DUR-A-WALL FGR

TECHNICAL INFORMATION

Toxicity Non-Toxic, USDA Approved		
Physical Property	Test Method	Result
Hardness, Shore D	ASTM D-2240	70-80
Water Absorption	ASTM D-570	0.04%
Flammability	ASTM D-635	Self-Extinguishing
Flame Spread / NFPA-101	ASTM E-84	Class A
Tensile Strength	ASTM-D 638	3000 psi
Flexural Strength	ASTM D-790	4000 psi
Impact Resistance	ASTM E695-03	
Alkyd/Latex Paint	(Soft Body Impact)	75 ft.lbs. 0.120" set
Dur-A-Wall		75 ft.lbs. 0.060" set
Dur-A-Wall FGR		90 ft.lbs. 0.100" set
Impact Resistance	USG Pipe Cap Test	
Alkyd/Latex Paint	(Hard Body Impact)	10 ft. lbs.
Dur-A-Wall		13 ft. lbs.
Dur-A-Wall FGR		25 ft. lbs
Impact Resistance	ASTM D- 2794 @25 inch lbs	
Alkyd/Latex Paint	(Indentation, Mils)	85
Dur-A-Wall		68
Dur-A-Wall FGR		35
Bond Strength to Substrates	ASTM D- 4541	Substrate Failure
Thermal Shock, 50 cycles of immersion in	MIL F 52505	No cracking or loss of
Chilled and Boiling water		adhesion
Abrasion Resistance, CS-17 Wheel, Wgt.	ASTM D- 4060	15 mg. loss
Loss 1000 gm. Load 1000 cycles		
VOC Content		42.49 g/l

CLEANING

This product is considered to be a low maintenance coating solution. Please refer to the master Cleaning Guidelines on our website.

CAUTION

Slight batch-to-batch color variations may occur. When ordering to match a previous color, inquire if the same batch number or quality control number is still available. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN.

Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.