



Protective & Marine Coatings

GENERAL POLYMERS® 3579 STANDARD EPOXY PRIMER/ BINDER

PART A **GP3579** **SERIES**
PART B **GP3579B01** **STANDARD HARDENER**

Revised September 23, 2014

PRODUCT INFORMATION

PRODUCT DESCRIPTION

GENERAL POLYMERS 3579 STANDARD PRIMER / BINDER is a high solids, clear or pigmented epoxy primer and binder resin. GENERAL POLYMERS 3579 STANDARD PRIMER / BINDER is available in clear, red, white and gray, has good blush resistance and is low in viscosity to promote penetration of the concrete substrate and excellent wetting of mortar aggregate.

ADVANTAGES

- Good blush resistance at room temperature
- Low modulus of elasticity, stress relieving
- Acceptable for use in USDA inspected facilities

TYPICAL USES

GENERAL POLYMERS 3579 STANDARD PRIMER / BINDER is an epoxy primer for coatings, slurries, mortar overlays, and patches. It can be also used as a binder resin. For slurries, mortar and patching systems. Suitable for use in the Mining & Minerals Industry.

LIMITATIONS

- Slab on grade requires vapor/moisture barrier.
- Surface must be clean and dry.
- Cool damp conditions may cause surface blushing.
- Substrate must be structurally sound and free of bond inhibiting contaminants.
- During installation and initial cure cycle substrate and ambient air temperature must be at a minimum of 50°F (10°C). Substrate temperature must be at least 5°F (3°C) above the dew point (for lower temperature installation contact your local representative).
- When required, adequate ventilation shall be provided and proper clothing and respirators worn.
- **Strictly adhere to published coverage rates.**

SURFACE PREPARATION

Proper inspection and preparation of the substrate to receive resinous material is critical. Read and follow the "Instructions for Concrete Surface Preparation" (Form G-1) for complete details.

PRODUCT CHARACTERISTICS

Color: Clear, Red, Gray, White
Mix Ratio: 2:1
Volume Solids: 96% ± 2%, mixed
Weight Solids: 96% ± 2%, mixed
VOC (EPA Method 24): <50 g/L mixed: 0.41 lbs/gal
Viscosity, mixed: 2,100 cps

Recommended Spreading Rate per coat:

	Minimum	Maximum
Wet mils (microns):	6 (150)	20 (500)
~Coverage sq ft/gal (m²/L):	varies according to usage	

Drying Schedule @ 6 mils (150 microns) wet:

@ 73°F (23°C)

To touch: 6-8 hours
To recoat: 10-20 hours
If maximum recoat time is exceeded, abrade surface before recoating. Drying time is temperature, humidity, and film thickness dependent.
Pot Life: gallon mass 25-30 minutes @ 73°F (23°C)

Shelf Life: Part A: 36 months, unopened
Part B (Standard): 36 months, unopened
Store indoors at 50°F (10°C) to 90°F (32°C)
Flash Point: >230°F (>110°C), ASTM D 93, mixed

PERFORMANCE CHARACTERISTICS

Test Name	Test Method	Results
Adhesion	ACI 503R	300 psi concrete failure
Compressive Strength	ASTM D 695	9,000 psi
Flammability		Self-extinguishing over concrete
Flexural Strength	ASTM D 790	6,000 psi
Hardness, Shore D	ASTM D 2240	75/65
Tensile Strength	ASTM D 638	3,000 psi



Protective & Marine Coatings

GENERAL POLYMERS® 3579 STANDARD EPOXY PRIMER/ BINDER

PART A
PART B

GP3579
GP3579B01

SERIES
STANDARD HARDENER

Revised September 23, 2014

PRODUCT INFORMATION

APPLICATION

• APPLICATION INSTRUCTIONS

1. Add 2 parts 3579A (resin) to 1 part 3579B (hardener) by volume. Mix with low speed drill and Jiffy blade for three minutes and until uniform. To insure proper system cure and performance, strictly follow mix ratio recommendations.

2. 3579 may be applied via spray, roller or brush. Apply evenly, with no puddles. Coverage will vary depending upon porosity of the substrate and surface texture.

3. 3579 application varies upon usage.

NOTE: Epoxy materials may tend to blush at the surface especially in humid environments. After the surface is primed and before installation of each subsequent coat, surface must be examined for blush (a whitish greasy film and/or low gloss). The blush must be completely removed prior to recoating using warm detergent water or through solvent wipe.

Epoxy materials will appear to be cured and dry to touch prior to full chemical cross linking. Allow epoxy to cure for 2-3 days prior to exposure to water or other chemicals for best performance.

ORDERING INFORMATION

Packaging:	
Part A:	1 gallon (3.8L) and 5 gallon (18.9L) containers
Part B:	1 gallon (3.8L) and 5 gallon (18.9L) containers
Weight:	9.4 ± 0.2 lb/gal; 1.13 Kg/L mixed, may vary by color

CLEANUP

Clean up mixing and application equipment immediately after use. Use toluene or xylene. Observe all fire and health precautions when handling or storing solvents.

SAFETY

Refer to the MSDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

MAINTENANCE

Occasional inspection of the installed material and spot repair can prolong system life. For specific information, Contact your Sherwin-Williams representative.

SHIPPING

• Destinations East of the Rocky Mountains are shipped F.O.B. Cincinnati, Ohio.

• Destinations West of the Rocky Mountains are shipped F.O.B. Victorville, California.

For specific information relating to international shipments, contact your local sales representative.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.