



## HYBRI-FLEX AQ w/ACCELERERA

### DESCRIPTION

HYBRI-FLEX AQ is a 100% solids low odor color quartz system. It is composed of a 1/8" POLY-CRETE MD SL body coat with a decorative quartz broadcast, 1/16" DUR-A-GLAZE #4 broadcast coat, and two ACCELERERA topcoats yielding a total system thickness of 1/4".

### BENEFITS

- VOC Compliant
- ADA Compliant
- Contributes to LEED Credits
- Meets USDA, FDA and CFIA standards
- Hygienic - Does Not Harbor Bacteria
- High Chemical Resistance
- High Abrasion Resistance
- Self-Priming for Most Applications
- Wide Service Temperature Range
- Can Be Applied To 5-7 Day Old Concrete

### LIMITATIONS

This product is best suited for application in temperatures between 60°F and 85°F. Substrate must be clean, sound and dry.

### TYPICAL USES

HYBRI-FLEX AQ is designed to protect concrete, polymer reinforced screeds, mild steel and water resistant plywood from chemical attack, corrosion, impact and thermal shock. It is also unaffected by freeze/thaw cycles.

- Aesthetic Considerations
- Malls
- Hospitals
- Labs
- Commercial Businesses

### COLORS

HYBRI-FLEX AQ is available in blended and solid colors and in two sizes (Q11 and Q28). Refer to Quartz Color Blends Selector Chart for standard quartz blends.

### PACKAGING & STORAGE CONDITIONS

POLY-CRETE MD SL is available in pre-measured kits that consists of resin, hardener and aggregate. DUR-A-GLAZE #4 is package in 1, 5, and 50 gallon containers ACCELERERA is available in pre-measured kits. HYBRI-FLEX AQ components must be stored dry. Do not allow resins to freeze. Do not store near open flame or food. The shelf life of this product is 6 months from ship date in the original unopened container.

### SURFACE PREPARATION

This product requires preparation in order to perform as expected. Surface must be profiled, clean, dry, oil free and sound. Please refer to the Surface Preparation Guide on our website for more information.

### APPLICATION METHOD

POLY-CRETE MD SL is applied to a properly prepared area at the required thickness using a "V" notched squeegee. The freshly placed material is then loop rolled into which the proper size quartz aggregate is broadcast to excess to achieve the desired profile. Allow a minimum of 6 hours for the Base Coat to cure before sweeping, sanding or vacuuming. A second quartz broadcast is delivered into DUR-A-GLAZE #4. Apply two ACCELERERA top coats to achieve the required finish. See Application Instructions on our website for a detailed installation procedure.

### GUIDE SPECIFICATIONS

This product is part of the DUR-A-FLEX family of polymer systems. Please contact DUR-A-FLEX for complete three part guide specs.

### DRAWINGS AND DETAILS

Standard CAD drawings and details are available for coves, drains, breaches, transitions, etc. Please refer to the master Drawings and Details guide for actual drawings.

### JOINT GUIDELINES

Refer to the Joint Guidelines for complete details on our website.

# HYBRI-FLEX AQ w/ACCELERA

## TECHNICAL INFORMATION

Physical Property	Test Method	Result
60 Gloss	ASTM D-523	90+
Impact Resistance	ASTM D-2794	>160
Bond Strength to Concrete	ASTM D-4541	400 psi (substrate fails)
Compressive Strength	ASTM D-695	17,500 psi
Solids by volume		100
Adhesion	ASTM D-4541	400 psi
Hardness	ASTM D-3363	3H
	ASTM D-2134	40+
QUV	UVB-373/1500hrs	>90% gloss retention
Flexibility (1/4: Cylindrical mandrel)	ASTM D-1737	Pass
Elongation	ASTM D-2370	9%
Tensile Strength	ASTM D-2370	7,000 psi
Coefficient of Friction	ASTM D-2047	>0.6
Abrasion Resistance CS17 wheel (1000g load) 1000 Cycles	ASTM D-4060	27 mg loss
Flame Spread Index	ASTM E84	Class B (Type II)
VOC Content		0 g/l

### MOISTURE CONCERNS

Normal limits for moisture vapor transmission for Hybri-Flex floor systems are 20 lbs./1,000 sq. ft./24 hour using the calcium chloride test per ASTM F-1869 or 99% relative humidity using in-situ Relative Humidity Testing per ASTM F-2170. Please refer to the Floor Evaluation Guidelines at [www.dur-a-flex.com](http://www.dur-a-flex.com) for complete details.

### CHEMICAL RESISTANCE

HYBRI-FLEX AQ has excellent resistance to organic and inorganic acids, alkalis, fuel and hydraulic oils, as well as aromatic and aliphatic hydrocarbons. Contact the Dur-A-Flex Technical Department for questions about specific chemicals.

### CLEANING

Regular scrubbing will maintain these systems in serviceable condition. However, certain textures and service environments require specific procedures. Please refer to the master Cleaning Guide on our website for more information.

### CAUTION

Read, understand and follow Material Safety Data Sheets and Application Instructions of this flooring system prior to use. Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed

*Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.*