

**PRODUCT DATA SHEET** 

95 Goodwin Street East Hartford, CT 06108

Tel: 800-253-3539 · Fax: 860-528-2802 · Internet: www.dur-a-flex.com · E-Mail: contact\_us@dur-a-flex.com

## **ULTRA CLEAR COVE-REZ**

#### **DESCRIPTION**

ULTRA CLEAR COVE-REZ resin is a thixotropic version of ULTRA CLEAR resin. This product was specifically designed for vertical applications where extra sag resistance is required. The viscosity drops significantly while mixing, which makes mixing and handling easy. When the mixing blade is removed the viscosity rises once again. This added viscosity makes cove work easier and more efficient, while maintaining the durability and chemical resistance found in DUR-A-GLAZE #4 "Regular" resin.

#### **BENEFITS**

- Excellent UV Resistance
- Low Odor
- Coves Close Up Tighter
- Versatile Usage
- Good Chemical Resistance
- Tenacious Bonding Quality

#### **COLORS**

ULTRA CLEAR COVE-REZ is clear and is not intended to be pigmented.

#### TYPICAL USES

This formula was developed <u>specifically</u> for installing cove and may be used in all phases of that process (Prime coat, Base coat, and Topcoat).

#### **SURFACE PREPARATION**

This product requires preparation in order to perform as expected. Substrate must be roughened, clean, sound, and dry. Please refer to the master Surface Preparation Guide on our website for more information.

#### APPLICATION METHOD -(blended COVE-REZ)

Prime the wall with a light coat of the mixed resin and hardener. Next, trowel up a mixture of 1.5 qts of epoxy to 8 qts DUR-A-QUARTZ Q-11 or Q-28. When that has cured, use a brush to topcoat. Be sure to remove any excess material with a squeegee. This should be done by pulling the material down to the bottom of the cove radius, then back up to the top edge of the cove. Do not apply on broadcast quartz floors. Because the surface is not smooth, the finish will appear white. Topcoat smooth troweled surfaces only. ULTRA CLEAR COVE-REZ is typically applied at 200-250 **linear feet** per gallon.

#### **LIMITATIONS**

This product is best suited for application in temperatures between  $55^{\circ}F$  and  $95^{\circ}F$ . Substrate must be clean, sound, and dry. Don't leave a heavy topcoat on cove base, pull excess sealer off with squeegee. If not removed, a milky white haze will remain on cove base.

#### PACKAGING

DUR-A-GLAZE COVE-REZ is available in 1-gallon cans, and 5-gallon pails.

<sup>&</sup>quot;Warranties: Seller warrants that its goods, as described on the face hereof, are free from any defects in material or workmanship. Seller makes no other warranty, express or implied, and all implied warranties of merchantability and fitness for a particular purpose are hereby disclaimed. Seller shall not be liable for prospective profits or special indirect or consequential damages. Seller's sole liability and buyer's exclusive remedy for breach of any warranty as expressly limited, at seller's option, to replacement at the original F.O.B. point or refund of purchase price. Seller shall not be responsible for any claim resulting from failure to utilize product in the manner in which it was intended and in accordance with instruction provided for use of product. Any claim for breach of warranty shall be deemed waived unless buyer shall give seller written notice of such claim within sixty (60) days after delivery and shall allow seller reasonable opportunity to investigate claim and inspect product."

# ULTRA CLEAR COVE-REZ

## TECHNICAL INFORMATION

Color	Clear	
Mix Ratio (by volume)	Combine 1 part hardener to 2 parts resin	
Viscosity at 70°F (mixed hardener & resin)	150,000 cps	
Thixotropic Index	3.4	
Pot Life at 70°F	30 - 35 minutes	
Cure Time, Touch Dry at 70°F	8 hours	
Cured Film Thickness	6 mils at 200 LF	
Toxicity.	Non-toxic. USDA compliant	
Physical Property	<b>Test Method</b>	Result
Hardness, Shore D	ASTM D-2240	80 - 85
Water Absorption	ASTM D-570	Nil
Tensile Strength	ASTM D-638	2,100 psi
Flexural Strength	ASTM D-790	5,100 psi
Compressive Strength	ASTM D-695	11,200 psi
Bond Strength to Concrete	ACI – 403	Concrete fails before loss of bond
Abrasion Resistance, CS-10 Wheel, Wgt. Loss, 1000 gr. Load, 1000 cycles		35 mg.
VOC Content		0 g/l

#### **MOISTURE CONCERNS**

Please refer to the Floor Evaluation Flow Chart in the Contractor's Center of our website for a step-by-step process to determine the condition of the concrete.

### **CAUTION**

Follow the Hazardous Materials Identification System labeling guide for proper personal protective equipment to use when handling this product. Use only as directed. KEEP OUT OF REACH OF CHILDREN.

Before using any DUR-A-FLEX, Inc. product, be sure the Material Safety Data Sheet is read and understood.