



The Chemical Company

Technical Data Guide



09 96 35
Chemical Resistant
Flooring

MasterTop[®] TC 565

Clear and tinted chemical resistance epoxy floor coatings

FORMERLY SELBY™ 600 SERIES COATINGS

PACKAGING

5 gallon (18.95 L) pails

COLOR

Clear and 7 standard colors (see the BASF Performance Flooring Color Guide for more information)

SHELF LIFE

2 years when properly stored

STORAGE

Store and transport in unopened containers in a clean, dry environment. Protect from freezing.

VOC CONTENT

See MasterTop TC 565 LEED Letter

DESCRIPTION

MasterTop TC 565 is a 100% solids epoxy polymer resin. It is specially formulated for areas requiring an increased level of chemical resistance.

PRODUCT HIGHLIGHTS

- High level of chemical resistance to protect floors from the harshest industrial environments
- 100% solids formulation that has virtually no odor and very low VOC
- Creates a hard surface that is easy to clean and maintain
- Available in textures, allowing slip resistance to be customized according to each facility's needs

APPLICATIONS

- Where harsh chemicals are used or stored
- Industrial plants
- Petrochemical facilities
- Battery manufacturing and storage areas
- Pulp and paper industries
- Electroplating operations
- Acid-etching environments
- Laboratories

LOCATION

- Interior

SUBSTRATE

- New and existing concrete surfaces and toppings

TECHNICAL DATA

COMPOSITION

MasterTop TC 565 is a 100% solids epoxy resin.

TYPICAL PROPERTIES

PROPERTY	VALUE
Tack free time , hrs.	4 – 6
Initial cure , hrs.	24

TEST DATA

PROPERTY	RESULTS	TEST METHODS
Abrasion Resistance , mg loss CS-17 Wheel, 1,000 g load 1,000 cycles	0.150	ASTM D4060
Pot Life , min.	40	ASTM D2471
Bond Strength , psi (MPa)	350 (2.4) 100% concrete failure	ASTM D4541
Compressive Strength , psi (MPa)	14,000 (96)	ASTM C579
Tensile Strength , psi (MPa)	3,000 (21)	ASTM D638
Elongation , %	1.0	ASTM D638
Hardness , Shore D	75 – 80	ASTM D2240

Unless otherwise noted, test samples were cured for 28 days at 70 °F (23 °C)

CHEMICAL RESISTANCE

CHEMICAL	RESISTANCE
Mineral Acids	Very Good
Fats, Oils and Sugars	Excellent
Organic solvents	Very Good
Alkalis	Very Good

Full chemical resistance is achieved after curing for 7 days. For resistance to a specific chemical compound, consult the MasterTop Chemical Resistance Guide.

HOW TO APPLY

1. Mix the components for this product in the following ratios:

TYPICAL PROPERTIES

COMPONENTS	MIX RATIO BY VOLUME
MasterTop TC 565 Part A /	
MasterTop TC 565 Part B	2 to 1

2. Mix each component separately before mixing together.
3. Combine parts A and B in a suitably sized container. Use the proper ratios of A and B; scrape the sides of the containers to ensure a complete reaction.
4. Mix properly for 3 minutes with a slow speed drill and Jiffy style mixing paddle at 350 rpm. Keep the paddle below the surface to avoid entrapping air. Do not mix by hand.

APPLICATION

Refer to the specific MasterTop epoxy floor coating system for specific application instructions relative to the use of these materials within the system.

DRYING TIME

Tack free: 4 to 6 hours

Accepts light traffic: 24 hours

Fully cured for chemical resistance: 7 days

Recoat window: 12 to 24 hours

Cure times are based on conditions at 70° F (21° C) and 50% ambient relative humidity. Lower temperatures will extend the cure times significantly.

MAINTENANCE

Regular cleaning and maintenance will prolong the life of all polymer flooring systems, enhance their appearance and reduce any tendency to retain dirt. Refer to the MasterTop Cleaning and Maintenance Guide for further information.

FOR BEST PERFORMANCE

- Precondition this product to 70° F (21° C) for 24 hours before using.
- Do not exceed the recommended recoat window of 24 hours. If in doubt, contact your BASF flooring specialist.
- Do not expose MasterTop TC 565 Coatings to any chemicals until fully cured (7 days).
- Use an effective moisture barrier for substrates on or below grade. If not present, contact your BASF representative for options.
- Install this product at a substrate temperature between 50 and 85° F (10 and 30° C)
- Textures can be varied using different aggregates.
- The architect and owner should address joint details with the contractor before the job starts.
- BASF representatives and floor specialists are available to assist you in the selection of the proper flooring system. Call 1-800-243-6739 for in-house and field technical assistance.
- Make certain the most current versions of product data sheet and SDS are being used; visit www.master-builders-solutions.BASF.us to verify the most current versions.
- Proper application is the responsibility of the user. Field visits by BASF personnel are for the purpose of making technical recommendations only and not for supervising or providing quality control on the jobsite.

HEALTH, SAFETY AND ENVIRONMENTAL

Health, Safety and Environmental Read, understand and follow all Safety Data Sheets and product label information for this product prior to use. The SDS can be obtained by visiting www.master-builders-solutions.basf.us, e-mailing your request to basfbscst@basf.com or calling 1(800)433-9517. Use only as directed. **For medical emergencies only, call ChemTrec 1(800)424-9300.**

LIMITED WARRANTY NOTICE

Every reasonable effort is made to apply BASF exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, BASF MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and BASF shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the BASF Technical Manager.

This information and all further technical advice are based on BASF's present knowledge and experience. However, BASF assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, BASF disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. BASF SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS)

OF ANY KIND. BASF reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.

FOR PROFESSIONAL USE ONLY. NOT FOR SALE TO OR USE BY THE GENERAL PUBLIC.

BASF Corporation
Constructions Systems

889 Valley Park Drive, Shakopee, MN 55379
www.master-builders-solutions.basf.us

Customer Service 1(800)433.9517
Technical Service 1(800)243.6739



BASF Constructions Systems, LLC
Registered in MN 08/11/2014
Certificate No. 414282