

07 10 00 Dampproofing and Waterproofing

07 19 23 Siloxane Water Repellents

09 60 00 Flooring

09 61 00 Flooring Treatments

PRODUCT DATA SHEET**PROSOCO**
SINCE 1939**CONSOLIDECK®**

Saltguard®

deeply penetrating water & salt barrier for concrete and masonry surfaces

OVERVIEW

Consolideck® Saltguard® is a general-purpose silane/siloxane water repellent and chloride screen for concrete and masonry, including concrete block, and clay and concrete brick surfaces. Saltguard® protects horizontal and vertical surfaces from moisture intrusion and chemical attack of chloride salts, reducing rebar corrosion and surface spalling.

Saltguard® may be used on horizontal surfaces such as sidewalks, tile and brick pavers. It also provides excellent protection for retaining walls, bridge pilings and other vertical areas. In coastal areas, Saltguard® protects against salt air by reducing chloride penetration. Saltguard® also prevents deep-seated staining by mud splashes and other waterborne contaminants.

SPECIFICATIONS

For all PROSOCO product specifications visit www.prosoco.com and click on "SpecBuilder" or "Solution Finder."

ADVANTAGES

- Non film-forming – will not create a slippery surface.
- Effective chloride ion screen protects against salts and salt air.
- Deep penetration.
- Alkaline stable – performs on new concrete where other treatments fail.
- Treated surfaces "breathe" – does not trap moisture.
- Low odor.

Limitations

- Not suitable for application to synthetic resin paints, gypsum, plaster or other non masonry surfaces.
- May not be suitable for surfaces receiving paints or coatings. Always test.
- May cause slight darkening on some surfaces.
- May adhere to glass. Contact PROSOCO for removal recommendations.
- Not suitable for protecting surfaces subject to constant water spray.
- Will not compensate for structural or material defects.
- Not recommended for below grade application.
- Not suitable for sale in states and districts with more restrictive AIM VOC regulations.

REGULATORY COMPLIANCE

VOC Compliance

Consolideck® Saltguard® is compliant with the following national, state and district AIM VOC regulations

- US Environmental Protection Agency
- California Air Resources Board SCM Districts
- South Coast Air Quality Management District
- Maricopa County, AZ
- Northeast Ozone Transport Commission

Manufactured and marketed in compliance with USEPA AIM VOC regulations (40 CFR 59.403).

TYPICAL TECHNICAL DATA

FORM	clear liquid
SPECIFIC GRAVITY	0.794
pH	Not applicable
WT/GAL	6.61 lbs
ACTIVE CONTENT	11%
TOTAL SOLIDS	9%
VOC CONTENT	>600 g/L
FLASH POINT	127°F (53°C) ASTM D 3278
FREEZE POINT	No data
SHELF LIFE	2 years in tightly-sealed, unopened container

PREPARATION

Protect people, vehicles, nearby property, metal and anodized aluminum, glass, plants and all non masonry from product, fumes, spray and wind drift. Divert and/or protect auto and pedestrian traffic. Protect window glass.

Ensure fresh air entry and cross ventilation during application and drying. Extinguish all flames, pilot lights and other potential sources of ignition during use and until all vapors are gone. When applying to exteriors of occupied buildings, make sure all windows, exterior intakes and air conditioning vents are covered and air handling equipment is shut down during application and until vapors have dissipated.

If possible, install all caulking, patching and joint sealants before applying Saltguard®. If impractical, special joint preparation may be required to ensure caulk adhesion.

For maximum penetration, clean surfaces thoroughly with the appropriate Consolideck® or Sure Klean® cleaner to remove all surface dirt, oil, grease and other contaminants.

New concrete should be thoroughly cured before application of Saltguard®. Do not attempt application where condensation is present.

Specifier's Note – Curing New Concrete:

Blanket or water curing is recommended whenever possible. Dissipating curing agents are recommended. Avoid over application of the curing agent. For best performance, remove all other surface films and contaminants before application of Saltguard®.

Surface and Air Temperatures

If freezing conditions exist before application, let masonry thaw. Best air and masonry surface temperatures for use are between 40–90°F (4–32°C). On warm days, apply early in the day and to shaded areas.

Equipment

Apply using low-pressure (<50 psi) spray, brush or roller. Sprayers must be fitted with solvent-resistant hoses and gaskets.

When using brushes or rollers, saturate the surface to the point of rejection.

When spray applying to fluted architectural block, spray in an “overlapping X pattern” for complete coverage of recessed surfaces.

Storage and Handling

Store in a cool, dry place away from potential ignition sources. Keep tightly sealed when not dispensing. Published shelf life assumes upright storage of factory-sealed containers in a dry place. Maintain temperature of 45–100°F (7–38°C). Do not double stack pallets. Dispose of unused product and container in accordance with local, state and federal regulations.

APPLICATION

Before use, read “Preparation” and “Safety Information.”

ALWAYS TEST each type of surface and coating for suitability and results before overall application. Test using the following application instructions. Let test area dry thoroughly before inspection.

Dilution

Use in concentrate. Do not dilute or alter. Stir or mix well before use.

Coverage Rates

Coverage varies based on substrate porosity and texture. Always test.

- 50–300 square feet per US gallon
- 5–28 square meters per US gallon

ALWAYS TEST

ALWAYS TEST a small area of each surface to confirm suitability and desired results before starting overall application. Test with the same equipment, recommended surface preparation and application procedures planned for general application.

Application Instructions

Vertical Surfaces

Apply with low-pressure (<50 psi) spray in a flooding application from the bottom up. Apply enough material for a rundown below the spray pattern. Brush out heavy runs and drips thoroughly so that the material completely penetrates the surface.

Porous surfaces will require a “wet-on-wet” application. Let the first application penetrate for 5 to 10 minutes and then reapply. Do not let any of the first application dry before making the second application. Less material will be required on the second application.

Horizontal Surfaces

Apply in a single, saturating application so that treated surfaces stay wet for a few minutes before penetrating. Broom out surface residues, pools and puddles until they completely penetrate the surface.

Drying Time

Protect treated surface from rain and pedestrian traffic for 4–6 hours following application. Protect treated surfaces from vehicular traffic for 8–12 hours after treatment. Saltguard® gains its water-repellency properties in 72 hours.

Cleanup

Clean tools and equipment immediately with mineral spirits.

Paint Adhesion

Surfaces treated with Saltguard® may be coated with most silicone emulsion and oil-based paints. Adhesion of some cementitious coatings, plaster, stucco, etc., may be adversely affected. Install such surface treatments and let them thoroughly cure before Saltguard® applications. Always test to verify compatibility between Saltguard® and other proposed surface treatments.

SAFETY INFORMATION

Consolideck® Saltguard® is a solvent carried product and may cause symptoms typical with organic solvent exposures. This is a combustible material. Use appropriate ventilation, safety equipment and job site controls during application and handling. Read the full label and MSDS for precautionary instructions before use.

First Aid

Ingestion: If swallowed, call a physician immediately. **ASPIRATION HAZARD:** Do not induce vomiting or give anything by mouth. Only induce vomiting at the instructions of a physician. If vomiting occurs, keep head below waist to prevent entry of liquid into lungs.

Eye Contact: Rinse eyes thoroughly for 15 minutes. Get medical assistance if irritation persists.

Skin Contact: Rinse thoroughly with soap and water. Remove contaminated clothing and launder before reuse. Get medical attention if irritation persists.

Inhalation: Remove to fresh air and provide oxygen if breathing is difficult. Give artificial respiration if not breathing. Get immediate medical attention.

24-Hour Emergency Information:
INFOTRAC at 800-535-5053

WARRANTY

The information and recommendations made are based on our own research and the research of others, and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

PROSOCO, Inc. warrants this product to be free from defects. **Where permitted by law, PROSOCO makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for particular purpose.** The purchaser shall be responsible to make his own tests to determine the suitability of this product for his particular purpose. PROSOCO's liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves PROSOCO from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability. This warranty may not be modified or extended by representatives of PROSOCO, its distributors or dealers.

CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Call 800-255-4255 and ask for Customer Care - technical support.

Factory-trained representatives are established in principal cities throughout the continental United States. Call Customer Care at 800-255-4255, or visit our web site at www.prosoco.com, for the name of the Consolideck® representative in your area.

BEST PRACTICES

Use the appropriate Consolideck® concrete prep cleaner to remove contaminants from existing concrete before applying Saltguard®. Stains and soiling may interfere with Saltguard® penetration.

For recommendations on removing stains and coatings, visit www.prosoco.com, call PROSOCO technical Customer Care toll-free at 800-255-4255 or contact your local PROSOCO field representative.

Preferred method of application is with low-pressure (<50 psi) spray, brush or roller. Sprayers must be fitted with solvent-resistant hoses and gaskets.

When using brushes or rollers, saturate the surface to the point of rejection.

When spray applying to fluted architectural block, spray in an "overlapping X pattern" for complete coverage of recessed surfaces.

Always saturate the surface uniformly. Give the treatment a few minutes to penetrate, but brush out pools and puddles quickly.

Never go it alone. If you have problems or questions, contact your local PROSOCO distributor or field representative. Or call PROSOCO technical Customer Care, toll-free, at 800-255-4255.

CONSOLIDECK®

Saltguard®

PRODUCT DATA SHEET

PROSOCO

SINCE 1939

This Page Intentionally Blank