

**Product Data Sheet**  
Edition 6.24.2014  
Sikafloor®-19NA PurCem®

# Sikafloor®-19NA PurCem®

Heavy Duty Trowel Applied Cementitious Urethane Mortar

**Description** Sikafloor-19NA PurCem is a trowel grade, heavy duty, solid color, three-component, water dispersed polyurethane-based / cement and aggregate screed designed to provide excellent resistance to abrasion, impact, chemical attack and other physical aggression. Sikafloor-19NA PurCem has a textured aggregate surface providing moderate slip resistance. Sikafloor-19NA PurCem Broadcast has a broadcast aggregate texture for increased slip resistance. Both systems are typically installed at 1/4 to 3/8 in (6 to 9 mm) thickness.

**Where to Use**

- Sikafloor-19NA PurCem is primarily used to protect concrete substrates.
- Typically used in food processing plants, wet and dry process areas, freezers and coolers, thermal shock areas, dairies, breweries, wineries, distilleries, laboratories, chemical process plants, pulp and paper plants, warehouses and storage areas.

**Advantages**

- Can be applied onto green concrete (typically 7 -10 days) after adequate preparation and where substrate has tensile bond strength in excess of 218 psi (1.5 MPa).
- Can be applied to concrete substrates where < 100% relative humidity is measured as per ASTM F2170.
- Resists a very wide range of organic and inorganic acids, alkalis, amines, salts and solvents. Consult Sika Technical Sales for full details. Refer to the Sikafloor PurCem Chemical Resistance Chart.
- Similar coefficient of thermal expansion to concrete allowing movement with the substrate through normal thermal cycling. It will perform and retain its physical characteristics through a wide temperature range from -40°F (-40°C) up to 248°F (120°C).
- Steam cleanable at 1/4 - 3/8 in (6 - 9 mm) thickness.
- Bond strength in excess of the tensile strength of concrete, concrete will fail first.
- Non-taint, odorless.
- Behaves plastically under impact / deforms but will not crack or debond.
- High abrasion qualities result from its aggregate structure.
- Can be applied over partially cured concrete substrates (<10% surface moisture), full 28 days cure time is not necessary.
- Extra Expansion joints are not necessary; maintain and extend existing expansion joints up through the Sikafloor PurCem Flooring System.
- Minimal maintenance costs, superior life cycle cost advantage versus tile.
- Achieves highest performance ratings according to ASTM G21 resistance to fungi and ASTM D3273 resistance to mold growth.
- Meets the requirements of USDA for use in food plants.

**TYPICAL DATA**  
RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

**Packaging** Component A: 1 US gal (3.78 L) 8.53 lb (3.87 kg)  
Component B: 0.7 US gal (2.64 L) 7.33 lb (3.325 kg)  
Component C: 2 x 39.7 lbs (18.02 kg) in bags (powder)  
Components A+B+C: 95.26 lb (43.23 kg)

**Colors** Standard colors: RAL 7046 Telegrey 2 RAL 3009 Oxide Red  
RAL 7038 Agate Gray RAL 7042 Traffic Grey A  
  
Color that requires lead time: RAL 1001 Beige  
Custom colors subject to minimum orders. Certain colors may require lead time

**Coverage** Approx. 31 ft² (2.8 m²) per unit at 1/4" (6 mm)  
Approx. 20 ft² (1.8 m²) per unit at 3/8" (9 mm)  
(The above figures do not allow for surface porosity, profile or wastage)

|                 |                             |                   |
|-----------------|-----------------------------|-------------------|
| <b>Pot Life</b> | <b>Material Temperature</b> | <b>Time</b>       |
|                 | +50°F (10°C)                | ~ 25 - 30 minutes |
|                 | +68°F (20°C)                | ~ 15 - 20 minutes |
|                 | +86°F (30°C)                | ~ 5 - 10 minutes  |

**Waiting / Recoat Times** Before applying Sikafloor-19NA PurCem in case a scratch primer is used allow:

|  |                |                |
|--|----------------|----------------|
| <b>Ambient &amp; Substrate Temperature</b> | <b>Minimum</b> | <b>Maximum</b> |
| +50°F (10°C)                               | 24 hours       | 7 days         |
| +68°F (20°C)                               | 6 hours        | 3 days         |
| +86°F (30°C)                               | 4 hours        | 2 days         |

|                   |  |                     |                      |                  |
|-------------------|--|---------------------|----------------------|------------------|
| <b>Cure Times</b> | <b>Ambient &amp; Substrate Temperature</b> | <b>Foot traffic</b> | <b>Light traffic</b> | <b>Full cure</b> |
|                   | +50°F (10°C)                               | ~ 24 hours          | ~ 6 days             | ~ 10 days        |
|                   | +68°F (20°C)                               | ~ 12 hours          | ~ 4 days             | ~ 7 days         |
|                   | +86°F (30°C)                               | ~ 6 hours           | ~ 2 days             | ~ 5 days         |

Industrial Flooring



# Industrial Flooring

## Properties Tested at 73° F (23° C) and 50% R.H:

|   |                 |  |
|---|-----------------|--|
| <b>Softening Point</b>                  |                 | 266°F (130°C)  |
| <b>Density</b>                          | ASTM C905       | 17.8 lb/US gal. (2.14 kg/L)  |
| <b>Flow</b>                             | Approx.         | 8.27 in (210 mm)   |
| <b>Service Temperature</b>              |                 | - 40°F (- 40°C) min. / 248°F (120°C) max.  |
| <b>Compressive Strength</b>             | ASTM 579        |  |
|   | 24 hrs          | 3,496 psi (24.1 MPa)   |
|   | 3 days          | 4,802 psi (33.1 MPa)   |
|   | 7 days          | 5,136 psi (35.4 MPa)   |
|   | 28 days         | 6,050 psi (41.7 MPa)   |
| <b>Tensile Strength</b>                 | ASTM C307       | 540 psi (3.7 MPa)  |
| <b>Flexural Strength</b>                | ASTM C580       | 1,572 psi (10.8 MPa)   |
| <b>Pull-off Strength</b>                | ASTM D4541      | > 254 psi (> 1.75 MPa) (substrate failure)   |
| <b>Thermal Compatibility</b>            | ASTM C884       | Pass   |
| <b>Shore D Hardness</b>                 | ASTM D2240      | 80 - 85  |
| <b>Indentation</b>                      | MIL -PRF -24613 | ~ 0%   |
| <b>Impact Resistance</b>                | ASTM D2794      | 4.18 ft - lb (5.67 joules)<br>at 1/8" (3 mm) of thickness  |
| <b>Abrasion Resistance</b>              | ASTM D4060      | CS-17/1,000 cycles/2.2 lb (1,000 g)<br>-0.006 oz (-0.155 g)<br>H-22/1,000 cycles/2.2 lb (1,000 g)<br>-0.077 oz (-2.18 g)   |
| <b>Coefficient of Friction</b>          | ASTM D1894-61T  | Steel 0.5<br>Rubber 0.7  |
| <b>Coefficient of Thermal Expansion</b> | ASTM D696       | 1.06 x 10 <sup>-5</sup> in/in/°F (1.9 x 10 <sup>-5</sup> mm/mm/°C)   |
| <b>Water Absorption</b>                 | ASTM C413       | 0.28%  |
| <b>Flexural Modulus</b>                 | ASTM C580       | 629,025 psi (4,335.7 MPa)  |
| <b>Resistance to Fungi Growth</b>       | ASTM G21        | Rated 0 (no growth)  |
| <b>Resistance to Mold Growth</b>        | ASTM D3273      | Rated 10 (highest resistance)  |
| <b>VOC's Components A+B+C:</b>          |                 | < 5 g/L  |
| <b>Shelf Life</b>                       |                 | Components A & B: 1 year in original unopened packaging.<br>Component C: 6 months in original unopened packaging.<br>Store dry between 50°- 75°F (10°- 25°C). Protect from freezing. |
| <b>Chemical Resistance</b>              |                 | Please consult Sikafloor Technical Services.   |

## How to Use Surface Preparation

Concrete surfaces must be clean and sound. Remove all dust, dirt, existing paint films, efflorescence, exudates, laitance, forms oils, hydraulic or fuel oils, brake fluid, grease, fungus, mildew, biological residues or any other contaminants which may prohibit good bond. Prepare the surface by any appropriate mechanical means, in order to achieve a profile equivalent to ICRI-CSP 3-6. The compressive strength of the concrete substrate should be at least 3,625 psi (25 MPa) at 28 days and a minimum of 218 psi (1.5 MPa) in tension at the time of application.

Repairs to cementitious substrates, filling of blowholes, leveling of irregularities, etc. should be carried out using an appropriate Sika profiling mortar. Contact Sika Technical Sales for a recommendation.

**Edge Terminations** - all free edges of a Sikafloor PurCem floor, whether at the perimeter, along gutters or at drains require extra anchorage to distribute mechanical and thermal stresses. This is best achieved by forming or cutting grooves in the concrete. Grooves should have a depth and width of 2 times the thickness of the Sikafloor PurCem floor. Refer to the edge details provided. If necessary, protect all free edges with mechanically attached metal strips. Do not featheredge, always turn into an anchor groove.

**Expansion Joints** - should be provided in the substrates at the intersection of dissimilar materials. Isolate areas subject to thermal stresses, vibration movements or around load-bearing columns and at vessel sealing rings. Refer to details.

## Priming

Substrate priming is normally not required under typical circumstances. Compressive strength of the concrete substrate of at least 3,625 psi (25 MPa) and at least 218 psi (1.5 MPa) in tension is required. However, due to variations in concrete quality, surface conditions, surface preparation and ambient conditions, reference test areas are recommended to determine whether priming is required to prevent the possibility of blisters, debonding, pinholes and other aesthetic variations.

Standard primer procedure consist of a 40 – 60 mils (1.0 - 1.5 mm) scratch coat of Sikafloor-31NA/24NA PurCem and light broadcasting of dry quartz sand. This is the preferred method for all substrates. The application is carried out using a steel trowel, ensuring a continuous coating is achieved.

## Mixing

**Mix Ratio:** Components A : B : C ("C" Consist of two bags of 39.7 lbs each) = **Mix full units only**

A "kol" type mixer, incorporating a motor spun mixing pail and a shear angle mixing blade, or a forced action mixer is recommended. Mixing will be affected by temperature; condition materials for use to 65 - 75° F (18 - 24° C). Premix Components A and B separately, make sure all pigment is evenly distributed. Pour Components A and B into a clean mixing bucket, and mix for 30 seconds. Add Component C (powder) pouring slowly over a period of 20 seconds. **Note: Do not dump powder into resin!** Allow Component C to blend for a further 2 1/2 minutes after all powder is emptied into the resin to ensure complete mixing and that all powders are wetted out. During the mixing operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing (Components A+B+C).

**Note:** Improved flowability on cool substrates can be achieved by removing a maximum of 2.2 lb (1.0 kg) of Component C (powder) per unit.

**Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.**



**Sika**®

**Application**

**Sikafloor-19NA PurCem:** trowel grade materials are applied with standard steel plastering or cement-finishing trowel 12 x 4 in (30 x 10 cm). Do not use serrated hand trowels. Priming of concrete substrates is not usually required under typical circumstances. However, due to variations in concrete quality, surface conditions, surface preparation and ambient conditions, reference test areas are recommended to determine whether priming is required to prevent the possibility of blisters, debonding, pinholes and other aesthetic variations.

Pour the material from the mixing pail, working to terminations or along the wet edge of previous pours. Using considerable top pressure on the trowel, spread material from side to side, pushing back into the previous mix (wet edge), pulling forward to establish the thickness and then, with a lighter pressure, trowel from side to side to close up. The last few strokes should always be in one direction only, left to right or right to left, but never back and forth. Excessive trowelling will bring the resin to the surface reducing the anti-slip surface.

**Sikafloor-19NA PurCem Broadcast:** mix and apply materials as outlined above in Mixing and Application. Sikafloor-19NA PurCem Broadcast requires quartz coloured aggregate to be broadcast on to the wet surface. Evenly distribute the matching solid colour aggregate by hand, covering all areas to avoid bald spots. Allow a minimum 10 hours cure at 68°F (20°C) before foot traffic. Alternatively, selected mineral aggregates can be broadcast on to the wet surface and sealed with a top coat of Sikafloor-31NA PurCem to lock in the aggregate. This application method requires a minimum 14 hours cure period at 68°F (20°C) before foot traffic, see Sikafloor-31NA PurCem Product Data Sheet.

**Limitations****Notes on Limitations:**

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

**Material Temperature:** Precondition material for at least 24 hours between 65° to 75°F (18° to 24°C). **IMPORTANT:** Product must be protected from freezing. If frozen, discard.

**Ambient Temperature:** Minimum/Maximum 50°/85°F (10°/30°C)

**Substrate Temperature:** Minimum/Maximum 50°/85°F (10°/30°C). Substrate temperature must be at least 5°F (3°C) above measured Dew Point.

Mixing and Application attempted at Material, Ambient and/or Substrate Temperature conditions less than 65°F (18°C) will result in a decrease in product workability and slower cure rates.

**Relative Ambient Humidity:** Minimum ambient humidity 30%  
Maximum ambient humidity 85% (during application and curing)

**Dew Point:** Beware of condensation!

The substrate must be at least 5°F (3°C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature. Calculate Dew Point from the substrate surface temperature, not the ambient temperature.

**Mixing:** Do not hand mix Sikafloor materials. Mechanically mix only.

Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. On no account should thinners be added to the mix. Adding thinners will void any applicable Sika warranty.

**Application:**

- Do not apply to polymer modified cement mortars (PCC) that may expand when sealed with an impervious resin.
- Do not apply to water-soaked, glistening-wet concrete substrates. (i.e standing water)
- Do not apply to un-reinforced sand cement screeds, asphaltic or bitumen substrate, glazed tile or non-porous brick, tile and magnesite, copper, aluminium, soft wood, or urethane composition, elastomeric membranes, fibre reinforced polyester (FRP) composites.
- Do not apply to cracked or unsound substrates.
- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.
- Freshly applied material should be protected from dampness, condensation and water for at least 24 hrs.
- Protect substrate during application from condensation from pipes or any overhead leaks.
- Do not apply to surfaces where moisture vapor can condense and freeze.
- Do not apply to vertical or overhead surfaces/ for vertical surfaces refer to Sikafloor-29NA PurCem.
- Do not featheredge.
- Applied material will follow undulations, depressions, lines, etc. of the underlying substrate. Visual appearance of the finished floor may vary, including, but not limited to, reflection of “waviness”, slab transitions, etc.
- Color uniformity cannot be completely guaranteed from batch to batch (numbered). Take care when using Sikafloor PurCem products to draw from inventory in batch number sequence, do not mix batch numbers in a single floor area.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings.

# Industrial Flooring

- Solid color UV resistant top coat available.
- Do not apply Sikafloor to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.
- Any aggregate used with Sikafloor systems must be non-reactive and oven-dried.
- This product is not designed for negative side waterproofing.
- For professional use only by experienced applicators.

|                             |   |
|-----------------------------|---|
| <b>Caution</b>              | <p><b>COMPONENT A: CAUTION: IRRITANT.</b> Contains Castor oil (CAS:8001-79-4), butane-1,4-diol (CAS:110-63-4), titanium dioxide (CAS:13463-67-7), Distillates (petroleum), hydrotreated middle (CAS:64742-46-7) and Carbon black (CAS:1333-86-4). Harmful if inhaled in high concentrations. May cause skin/eye/respiratory tract irritation. May cause gastrointestinal disturbance if swallowed. Reports have associated repeated and prolonged exposure to some of the chemicals in this product with permanent brain, liver, kidney and nervous system damage. <b>Intentional misuse by deliberate concentration and inhalation of vapors may be harmful or fatal. WARNING!</b> This product contains a chemical known in the State of California to cause cancer.</p> <p><b>COMPONENT B: WARNING: IRRITANT, SENSITIZER.</b> Contains methylenediphenyl diisocyanate (CAS:26447-40-5) and diphenylmethanediisocyanate, isomeres and homologues (CAS:9016-87-9). Harmful if inhaled/swallowed. Causes skin/eye/respiratory tract irritation. May cause allergic skin/respiratory reaction after prolonged contact. <b>Deliberate misuse by inhalation of vapors may be harmful or fatal.</b></p> <p><b>COMPONENT C: WARNING: IRRITANT.</b> Contains quartz (CAS:14808-60-7), and Portland Cement (CAS:65997-15-1). Causes severe eye irritation. May cause eye injury, effects may be delayed. May cause skin/respiratory tract irritation. May cause gastrointestinal disturbance if swallowed. <b>WARNING!</b> This product contains a chemical known in the State of California to cause cancer and birth defects or other reproductive harm.</p> |
| <b>First Aid</b>            | <p><b>Eyes</b> – Hold eyelids apart and flush thoroughly with water for 15 minutes. <b>Skin</b> – Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. <b>Inhalation</b> – Remove to fresh air. <b>Ingestion</b> – Do not induce vomiting. Dilute with water. Contact physician. <b>In all cases contact a physician immediately if symptoms persist.</b></p>   |
| <b>Handling and Storage</b> | <p>Avoid direct contact. Wear personal protective equipment (chemical resistant goggles/gloves/clothing) to prevent direct contact with skin and eyes. Use only in well ventilated areas. Open doors and windows during use. Use a properly fitted NIOSH respirator if ventilation is poor. Wash thoroughly with soap and water after use. Remove contaminated clothing and laundry before reuse.</p>   |
| <b>Clean Up</b>             | <p>Use personal protective equipment (chemical resistant gloves/goggles/clothing). Without direct contact, sweep up spilled or excess product and place in suitable sealed container. Dispose of excess product and container in accordance with applicable local, state, and federal regulations.</p>  |

**KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY**

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at [www.sikausa.com](http://www.sikausa.com) or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Material Safety Data Sheet which are available online at [www.sikausa.com](http://www.sikausa.com) or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Material Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at [www.sikausa.com](http://www.sikausa.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537

