

**Product Data Sheet**  
Edition 4.26.2013  
Sikafloor® 510 LPL

# Sikafloor® 510 LPL

## Abrasion and UV Resistant Polyaspartic Resin System

**Description** Sikafloor 510 LPL is a clear two-component, high solids, low-viscosity, high strength, fast cure, UV resistant, polyaspartic urethane coating system. Sikafloor 510 LPL has an extended working time and usable Pot-Life when compared to Sikafloor 510 especially in hot and humid conditions.

**Where to Use** It can be used as a concrete primer, binder, and sealer when fast cure times and UV resistance are required.

- Advantages**
- Resists a very wide range of organic and inorganic acids, alkalis, amines, salts and solvents.
  - Cures quickly, fast turnaround
  - Extended working time
  - Durable, impermeable and seamless
  - Superior mechanical resistance.
  - Excellent UV resistance
  - Excellent chemical resistance
  - Superior aesthetic finish.
  - Low maintenance.

### TYPICAL DATA

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

<b>Packaging</b>	Component A: 5 US gal. (18.9 L)	Component A: 5 US gal. (18.9 L) (3 Units needed)
	Component B: 3.33 US gal. (12.6 L)	Component A: 5 US gal. (18.9 L) (2 Units needed)
	Components A+B: 8.33 US gal. (31.5 L)	Components A+B: 25 US gal. (94.5 L)

**Color** Clear or pigmented with Sikafloor Urethane Color Additive; 1 quart (1.0 L) size.

**Coverage** **Smooth Finish Coating:**  
**Prime coat:** 160 - 200 ft<sup>2</sup> / US gal (3.9 - 4.9 m<sup>2</sup> / L) at 8 - 10 mils (0.20 - 0.25 mm) wet film thickness (w.f.t.)  
**Wear coat:** 105 - 135 ft<sup>2</sup> / US gal (2.6 - 3.3 m<sup>2</sup> / L) at 12 - 15 mils (0.30 - 0.38 mm) wet film thickness (w.f.t.)

<b>Pot Life</b>	<b>Material Temperature</b>	<b>Time</b>
	+50°F (10°C)	~ 40 minutes
	+68°F (20°C)	~ 30 minutes
	+86°F (30°C)	~ 20 minutes

\*Pot Life is based on clear resin, Urethane color additives can shorten the working time of Sikafloor 510 LPL.

<b>Waiting / Recoat Times</b>	Before applying second coat of Sikafloor 510 LPL allow:		
	<b>Ambient &amp; Substrate Temperature</b> +68°F (20°C)	<b>Minimum</b> 90 minutes	<b>Maximum</b> 24 hours

<b>Cure Times</b>	<b>Ambient &amp; Substrate Temperature</b> +68°F (20°C)	<b>Foot traffic</b> ~ 4 hours	<b>Light traffic</b> ~ 8 hours	<b>Full cure</b> ~ 5 days
-------------------	--	----------------------------------	-----------------------------------	------------------------------

**Properties Tested at 73°F (23°C) and 50 % R.H:**

<b>Tensile Strength</b>	ASTM C307	2,500 psi
<b>Pull-off Strength</b>	ASTM D4541	> 400 psi (2.7 MPa) (100% concrete failure)
<b>Elongation</b>	ASTM D638	60%
<b>Shore D Hardness</b>	ASTM D2240	75
<b>Abrasion Resistance by Taber Abraser</b> (CS-17 wheel, 1000 cycles, 1000 gm load)	ASTM D4060	50 mg loss
<b>VOC Content</b>	ASTM D2369	≤ 100 g/L
<b>Viscosity</b>	Components A + B mixed:	450 cps
<b>Application Temperature</b>	40°F min., 85°F max. (4°C min., 30°C max.)	
<b>Shelf Life</b>	Shelf Life 1 years in original, unopened packaging. Store dry at 40° - 90°F (4° - 32°C). Condition product between 65° - 85°F (18° - 30°C) before using.	
<b>Chemical Resistance</b>	Please consult Sikafloor Technical Services.	

Industrial Flooring



# Industrial Flooring

## How to Use Surface Preparation

Surface must be clean, sound and dry. Remove dust, laitance, grease, curing compounds, bond inhibiting impregnations, waxes and any other contaminants. All projections, rough spots, etc. should be dressed off to achieve a level surface prior to the application. **Concrete** - Should be cleaned and prepared to achieve a laitance-free and contaminant-free, open textured surface by shot blasting or equivalent mechanical means (CSP-3 to CSP-4 as per ICRI guidelines). Sweep and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual dust will help ensure a tenacious bond between the primer and substrate.

Whenever "shot-blasting" is utilized, be careful to leave concrete with a uniform texture. "Over-blasting" will result in reduced coverage rates of the primer and/or subsequent topcoats. The "shotblast" pattern may show through the last coat, known as "tracking". The compressive strength of the concrete substrate should be at least 3,500 psi (24 MPa) at 28 days and at least 250 psi (1.7 MPa) in tension at the time of application. For other substrates, please contact Sikafloor Technical Services.

## Priming

Priming for concrete substrate is required. Prime with either **Sikafloor 107, Sikafloor 160, Sikafloor 161 or Sikafloor 1610**. Allow the primer to cure (varies with temperature and humidity) until tack free before applying subsequent coats. Ensure that the primer is pore-free, pinhole-free and provides uniform and complete coverage over the entire substrate. In case of using Sikafloor 510 LPL as primer extra precaution has to be taken on the substrate preparation and on the moisture content.

## Mixing

### Mixing Ratio - 3 : 2 by volume.

For bulk packaging, when not mixing full units, each component must be pre-mixed separately to ensure product uniformity.

### Clear Resin:

Premix each Component separately. Empty Component B (Hardener) in the correct mix ratio into Component A (Resin). Mix the combined components for at least 3 minutes using a low speed drill (300 - 450 rpm) and Exomixer or Jiffy type paddle suited to the volume of the mixing container to minimize entrapped air. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

### Field Pigmented:

If color is desired, the appropriate Sikafloor Urethane Color Additive is added to Component A at a rate of 1 quart per 3 mixed gallons (i.e. Components A+B) for all colors. Mix Component A and Sikafloor Urethane Color Additive for 2 minutes or until a uniform color is achieved with a low speed drill (300 - 450 rpm) and Exomixer or Jiffy type paddle suited to the volume. Empty component B (Hardener) in the correct mix ratio to Component A (Resin) and mix for additional 2 minutes. Be careful not to introduce any air bubbles while mixing. Make sure the contents are completely mixed to avoid any weak or partially cured spots in the coating. During the mixing operation, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once to ensure complete mixing.

**\*Urethane color additive can shorten the working time (Pot Life) of Sikafloor 510 LPL.**

**Do not mix more material than can be applied within the working time limits (i.e. Pot Life) at the actual field temperature.**

## Application

### As a pigmented topcoat/sealer coat for smooth or broadcast finish:

Squeegee and roll apply Sikafloor 510 LPL to provide a uniform coverage without ponding at a thickness of 10 - 15 mils (160 - 107 ft<sup>2</sup>/gal). If required, repeat this procedure for a second coat.

### As a clear topcoat for a broadcast quartz or flake system:

Squeegee and roll apply Sikafloor 510 LPL to provide a uniform coverage without ponding at a thickness of 10 - 15 mils (160 - 107 ft<sup>2</sup>/gal). If required, repeat this procedure for a second coat.

### As a stand alone double broadcast quick cure decorative quartz and flake system:

**Step 1: Primer** - Apply neat Sikafloor 510 LPL on prepared substrate as a primer using a squeegee and roller without ponding at 5 - 10 mils (160 - 320 ft<sup>2</sup>/gal).

**Note:** When using Sikafloor 510 LPL as primer extra precaution has to be taken on the substrate preparation and moisture content.

**Step 2: First Broadcast Application** - Squeegee and roll apply Sikafloor 510 LPL to provide a uniform coverage without ponding at a thickness of 10 - 15 mils (160 - 107 ft<sup>2</sup>/gal). Broadcast pre-blended decorative flakes or colored quartz aggregates into the binder to saturation. Broadcast in a manner so that aggregates fall vertically into the binder. Broadcast to rejection. Ensure that broadcast flakes/aggregates cover entire surface. Allow broadcast system to cure sufficiently to be able to resist foot traffic without damaging the surface. Remove excess flakes/aggregates from the surface. Removal of excess flakes/aggregates is carried out by sweeping up the flakes/aggregates, followed by vacuuming, until surface is free of all loose particles and dust.



**Sika**®

**Step 3: Second Broadcast Application** - Squeegee and roll apply Sikafloor 510 LPL to provide a uniform coverage without ponding at a thickness of 10 - 15 mils (160 - 107 ft<sup>2</sup>/gal). Broadcast pre-blended decorative flakes or colored quartz aggregates into the binder to saturation. Broadcast in a manner so that aggregates fall vertically into the binder. Broadcast to rejection. Ensure that broadcast flakes/aggregates cover entire surface. Allow broadcast system to cure sufficiently to be able to resist foot traffic without damaging the surface. Remove excess flakes/aggregates from the surface. Removal of excess flakes/aggregates is carried out by sweeping up the flakes/aggregates, followed by vacuuming, until surface is free of all loose particles and dust.

**Step 4: Finish Coat** - Squeegee and roll apply Sikafloor 510 LPL to provide a uniform coverage without ponding at a thickness of 10 - 15 mils (160 - 107 ft<sup>2</sup>/gal). When required, repeat this procedure for a second coat.

## Limitations

### Notes on Limitations:

Prior to application, measure and confirm Substrate Moisture Content, Ambient Relative Humidity, Ambient and Surface Temperature and Dew Point. During installation, confirm and record above values at least once every 3 hours, or more frequently whenever conditions change (e.g. Ambient Temperature rise/fall, Relative Humidity increase/decrease, etc.).

**Substrate Moisture Content:** Moisture content of concrete substrate must be ≤ 4% by mass (pbw – part by weight) as measured with a Tramex® CME/CMExpert type concrete moisture meter on mechanically prepared surface according to this product data sheet (preparation to CSP-3 to CSP-4 as per ICRI guidelines). Do not apply to concrete substrate with moisture levels > 4% mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter. If moisture content of concrete substrate is > 4% by mass (pbw – part by weight) as measured with Tramex® CME/CMExpert type concrete moisture meter, use Sikafloor 1610 or Sikafloor 81 EpoCem.

When relative humidity tests for concrete substrate are conducted per ASTM F2170 for project specific requirements, values must be ≤ 85%. If values are > 85% according to ASTM F2170 use Sikafloor 1610 or Sikafloor 81 EpoCem.

ASTM F2170 testing is not a substitute for measuring substrate moisture content with a Tramex® CME/CMExpert type concrete moisture meter as described above.

**Material Temperature:** Precondition material for at least 24 hours between 65° to 75°F (18° to 24°C)

**Ambient Temperature:** Minimum/Maximum 50°/85°F (10°/30°C)

**Substrate Temperature:** Minimum/Maximum 50°/85°F (10°/30°C). Substrate temperature must be at least 5°F (3°C) above measured Dew Point.

Mixing and Application attempted at Material, Ambient and/or Substrate Temperature conditions less than 65°F (18°C) will result in a decrease in product workability and slower cure rates.

**Relative Ambient Humidity:** Minimum ambient humidity 30%

Maximum ambient humidity 75% (during application and curing)

**Note:** Low Relative Ambient Humidity may result in slower cure.

**Dew Point:** Beware of condensation!

The substrate must be at least 5°F (3°C) above the Dew Point to reduce the risk of condensation, which may lead to adhesion failure or “blushing” on the floor finish. Be aware that the substrate temperature may be lower than the ambient temperature.

**Mixing:** Do not hand mix Sikafloor materials. Mechanically mix only.

Do not thin this product. Addition of thinners (e.g. water, solvent, etc.) will slow cure and reduce ultimate properties of this product. Use of thinners will void any applicable Sika warranty.

**Application:** If Sikafloor 510 LPL is used as a primer, apply the coating to the prepared substrate using a squeegee and back roll to provide uniform coverage. Ensure that the substrate is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate. If necessary, apply an additional coat to ensure the substrate is pore-free and pinhole-free and provides uniform and complete coverage over the entire substrate.

- Do not apply while ambient and substrate temperatures are rising, as pinholes may occur. Ensure there is no vapor drive at the time of application. Refer to ASTM D4263, may be used for a visual indication of vapor drive.
- Freshly applied material should be protected from dampness, condensation and water for at least 72 hrs.
- Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. Use of clear UV resistant top coat may not prevent discoloration of underlying coatings.
- Do not apply Sikafloor to concrete substrate containing aggregates susceptible to ASR (Alkali Silica Reaction) due to risk of natural alkali redistribution below the Sikafloor product after application. If concrete substrate has or is suspected to have ASR (Alkali Silica Reaction) present, do not proceed. Consult with design professional prior to use.

## Industrial Flooring

- Any aggregate used with Sikafloor systems must be non-reactive and oven-dried.
- This product is not designed for negative side waterproofing.
- Typically not recommended for exterior slabs on grade where freeze/thaw conditions may exist.
- Use of unvented heaters and certain heat sources may result in defects (e.g. blushing, whitening, debonding, etc.).
- Beware of air flow and changes in air flow. Introduction of dust, debris, and particles, etc. may result in surface imperfections and other defects.
- For professional use only by experienced applicators.

**Caution**

**COMPONENT A: WARNING: CORROSIVE, IRRITANT, SENSITIZER.** Avoid direct contact. Contains Proprietary Blend of Amines (Mixture), Xylene (CAS: 1330-20-7), Diethyl fumarate (CAS: 623-91-6), Distillates (petroleum), hydrotreated light (CAS: 64742-47-8) and Ethylbenzene (CAS: 100-41-4). Corrosive to the respiratory system. Causes irritation to eyes/skin. Harmful if swallowed. May cause burns to mouth, throat, and stomach. May cause respiratory/skin sensitization. **Deliberate misuse by inhalation of vapors may be harmful or fatal. Strictly follow all usage, handling and storage instructions.** Reports have associated repeated and prolonged exposure to some of the chemicals in this product with permanent brain, liver, kidney and nervous system damage. **Intentional misuse by deliberate concentration and inhalation of vapors may be harmful or fatal. WARNING:** This product contains a chemical known to the State of California to cause cancer.

**COMPONENT B: WARNING: IRRITANT, SENSITIZER.** Contains Poly(hexamethylene diisocyanate) (CAS: 28182-81-2), xylene (CAS: 1330-20-7), ethylbenzene (CAS: 100-41-4) and hexamethylene-di-isocyanate (CAS: 822-06-0). Causes eye/skin/respiratory irritation. May cause respiratory/skin sensitization. Harmful if swallowed. Reports have associated repeated and prolonged exposure to some of the chemicals in this product with permanent brain, liver, kidney and nervous system damage. **Intentional misuse by deliberate concentration and inhalation of vapors may be harmful or fatal. WARNING:** This product contains a chemical known to the State of California to cause cancer.

**First Aid**

**Eyes** – Hold eyelids apart and flush thoroughly with water for 15 minutes. **Skin** – Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. **Inhalation** – Remove to fresh air. **Ingestion** – Do not induce vomiting. Dilute with water. Contact physician. **In all cases, contact a physician immediately if symptoms persist.**

**Handling & Storage**

Avoid direct contact. Wear personal protective equipment (chemical resistant goggles/gloves/clothing) to prevent direct contact with skin and eyes. Use only in well ventilated areas. Open doors and windows during use. Use a properly fitted NIOSH respirator if ventilation is poor. Wash thoroughly with soap and water after use. Remove contaminated clothing and launder before reuse.

**Clean Up**

**COMPONENT A:** Avoid contact. Wear chemical resistant clothing/gloves/goggles. In absence of adequate ventilation; use a properly fitted NIOSH respirator. Uncured material can be removed with approved solvent. Follow solvent manufacturer's instructions for use and warnings. In case of spill, ventilate area and contain spill. Collect with absorbent material. Dispose of in accordance with current, applicable local, state, and federal regulations.

**COMPONENT B:** Use personal protective equipment (chemical resistant gloves/ goggles/ clothing). Without direct contact, sweep up spilled or excess product and place in suitable sealed container. Dispose of excess product and container in accordance with applicable local, state, and federal regulations.

**KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY**

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at [www.sikausa.com](http://www.sikausa.com) or by calling 800-933-7452.

**Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Material Safety Data Sheet which are available online at [www.sikausa.com](http://www.sikausa.com) or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Material Safety Data Sheet prior to product use.**

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Visit our website at [www.sikausa.com](http://www.sikausa.com)

1-800-933-SIKA NATIONWIDE

**Regional Information and Sales Centers.** For the location of your nearest Sika sales office, contact your regional center.

**Sika Corporation**  
201 Polito Avenue  
Lyndhurst, NJ 07071  
Phone: 800-933-7452  
Fax: 201-933-6225

**Sika Canada Inc.**  
601 Delmar Avenue  
Pointe Claire  
Quebec H9R 4A9  
Phone: 514-697-2610  
Fax: 514-694-2792

**Sika Mexicana S.A. de C.V.**  
Carretera Libre Celaya Km. 8.5  
Fracc. Industrial Balvanera  
Corregidora, Queretaro  
C.P. 76920  
Phone: 52 442 2385800  
Fax: 52 442 2250537

