Product Data Sheet Edition 1.9.2012 Sikafloor FTP



## Sikafloor<sup>®</sup> FTP

Fast Track Primer

Description			
	Sikafloor FTP is a two-component, waterborne epoxy diluted with water in the field.		
Where to Use	Use with Sikalastic Traffic Systems as a primer on concrete, cementitious or plywood surfaces exposed to vehicular or pedestrian traffic. Refer to the Sikalastic 710/715 Traffic System and Sikalastic 720/745 Traffic System Product Data Sheets for system application instructions as well as limitations.		
Advantages	<ul> <li>Low VOC</li> <li>Fast dry time</li> <li>Low odor</li> <li>Moisture tolerant</li> </ul>		
Chemical	No Chemical Resistance Guide for this product, requires over coating with a Sika waterproofing		
Resistance	or flooring product or system.		
How to Use			
Surface Preparation	Concrete surface must be clean, sound and dry. Remove dust, laitance, grease, curi compounds, bond inhibiting impregnations, waxes and any other contaminants. All prough spots, etc. should be dressed off to achieve a level surface prior to the applicat Concrete should be cleaned and prepared to achieve a laitance and contaminant free textured surface by shot blasting to a minimum of (CSP-3-4 as per ICRI guidelines). and vacuum any remaining dirt and dust with a wet/dry vacuum. Removing residual of help ensure a tenacious bond between the primer and substrate. The compressive s the concrete substrate should be at least 3500 psi at 28 days and at least 250 psi in the time of application of Sikafloor FTP.		
	help ensure a tenacious bond the concrete substrate should	I between the primer and substrate. The compressive strength of I be at least 3500 psi at 28 days and at least 250 psi in tension a	
	help ensure a tenacious bond the concrete substrate should	I between the primer and substrate. The compressive strength of I be at least 3500 psi at 28 days and at least 250 psi in tension a	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON STA	I between the primer and substrate. The compressive strength of I be at least 3500 psi at 28 days and at least 250 psi in tension a	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON STA	d between the primer and substrate. The compressive strength of d be at least 3500 psi at 28 days and at least 250 psi in tension a affloor FTP.	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON STA TEMPERATURE, APPLICATION METHOD Shelf Life Pot Life	<ul> <li>a between the primer and substrate. The compressive strength of the at least 3500 psi at 28 days and at least 250 psi in tension a afloor FTP.</li> <li>ATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, is, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.</li> <li>2 years in original unopened container under proper storage conditions. Store dry between 40° - 90°F (5°- 32°C). Approx. 1 hour @ 77°F (25°C) and 50% relative humidity</li> </ul>	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON STA TEMPERATURE, APPLICATION METHOD Shelf Life	d between the primer and substrate. The compressive strength of d be at least 3500 psi at 28 days and at least 250 psi in tension a afloor FTP. ATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, is, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS. 2 years in original unopened container under proper storage conditions. Store dry between 40° - 90°F (5°- 32°C).	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON STA TEMPERATURE, APPLICATION METHOD Shelf Life Pot Life Packaging	<ul> <li>d between the primer and substrate. The compressive strength of d be at least 3500 psi at 28 days and at least 250 psi in tension a afloor FTP.</li> <li>ATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, is, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.</li> <li>2 years in original unopened container under proper storage conditions. Store dry between 40° - 90°F (5°- 32°C). Approx. 1 hour @ 77°F (25°C) and 50% relative humidity Sikafloor FTP is packaged in pre-proportioned kits. The kit consists of a gallon can of Resin and a short-filled five gallon pail of Hardener. The kit will yield 3.5 gallons of mixed product after the required reduction with water. ASTM D2369-07 0.2 g/l</li> </ul>	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON ST. TEMPERATURE, APPLICATION METHOD Shelf Life Pot Life Packaging VOC (g/l) Flash Point	<ul> <li>d between the primer and substrate. The compressive strength of d be at least 3500 psi at 28 days and at least 250 psi in tension a afloor FTP.</li> <li>ATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, is, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.</li> <li>2 years in original unopened container under proper storage conditions. Store dry between 40° - 90°F (5°- 32°C).</li> <li>Approx. 1 hour @ 77°F (25°C) and 50% relative humidity Sikafloor FTP is packaged in pre-proportioned kits. The kit consists of a gallon can of Resin and a short-filled five gallon pail of Hardener. The kit will yield 3.5 gallons of mixed product after the required reduction with water.</li> <li>ASTM D2369-07 0.2 g/l &gt;200°F (93.3°C)</li> </ul>	
	help ensure a tenacious bond the concrete substrate should the time of application of Sika Typical Data RESULTS MAY DIFFER BASED UPON STA TEMPERATURE, APPLICATION METHOD Shelf Life Pot Life Packaging	<ul> <li>d between the primer and substrate. The compressive strength of d be at least 3500 psi at 28 days and at least 250 psi in tension a afloor FTP.</li> <li>ATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, is, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.</li> <li>2 years in original unopened container under proper storage conditions. Store dry between 40° - 90°F (5°- 32°C). Approx. 1 hour @ 77°F (25°C) and 50% relative humidity Sikafloor FTP is packaged in pre-proportioned kits. The kit consists of a gallon can of Resin and a short-filled five gallon pail of Hardener. The kit will yield 3.5 gallons of mixed product after the required reduction with water. ASTM D2369-07 0.2 g/l</li> </ul>	





Mixing	<ul> <li>It is important to remember that this coating has a limited pot life of approximately 1 hour at 77°F (25°C) and 50% relative humidity. Do not use beyond this frame regardless of whether or not the product appears to still be usable. Review that all surface preparation is complete and application equipment is in good working order before starting the mixing sequence.</li> <li>1. Premix each component for a maximum of two minutes. Sikafloor FTP, Part "H" is dark olive green in color and may appear black in the container. Sikafloor FTP, Part "R" is light amber in color.</li> <li>2. Add the 1 gallon of Sikafloor FTP, Part "R" to the 1.25 gallons of Part "H" in the short filled Part "H" pail.</li> <li>3. Mix thoroughly with a Jiffy blade for a minimum of 3 minutes. The mixture will appear as a uniform light olive green color.</li> <li>4. Slowly add 1.25 gallons of potable water to the mixture under agitation.</li> <li>5. Mix for a minimum of 2 additional minutes until the mixture is fully dispersed. Fully dispersed material will appear as light yellow to white in color.</li> </ul>		
	<b>NOTE:</b> The order that the FTP components are mixed is critical to the performance of this product. Failure to mix properly may result in an incomplete cure, despite a dry appearance.		
Application	Apply with flat squeegee or roller at the recommended rate. Allow for sufficient wetting of the slab and backroll, utilizing a ¼" or ¾" nap roller to eliminate puddles on the surface of the slab. Minimize the overlap from batch to batch or bead-to-bead applications while achieving complete slab coverage, as these areas of overlap may not bond.		
Critical Recoat Time	Sikafloor FTP has a recoat window of up to 48 hours. Do not apply a second coat of Sikafloor FTP, as it will not properly bond. There is no need for additional mechanical or chemical preparation of the Fast Track Primer prior to the installation of the topcoat, if recoated with in the recoat window, and the Sikafloor FTP has not been exposed to foot or vehicular traffic or similar. If the recoat window is missed (48 hours) the surface requires grinding or screening with 80 grit, followed by a broom sweep and vacuum.		
Limitations	<ul> <li>IMPORTANT: Product must be protected from freezing. If frozen, discard.</li> <li>Minimum/Maximum substrate temperature: 40°F/90°F (4°C/32°C).</li> <li>Maximum ambient relative humidity must be no more than 85%.</li> <li>Substrate temperature must be 5°F (3°C) above measured dew point.</li> <li>This product is not designed for immersion or any use where moisture can reach the underside of the resurfacer.</li> <li>Freshly applied Sikafloor FTP should be protected from freezing, dampness, condensation and water prior to top coating.</li> <li>Will discolor over time when exposed to sunlight (UV) and under certain artificial lighting conditions. UV resistant, light stable topcoats are available where ultimate color/clarity retention is required.</li> <li>This product may not effectively bond to very dense, burnished or over finished concrete. Finishing should be limited to the degree that the floor flatness factor is achieved.</li> </ul>		
Caution	<ul> <li>COMPONENT A: WARNING - IRRITANT, SENSITIZER: Contains epoxy resins, Nonyl Phenol (CAS 25154-52-3). Eye irritant. May cause skin/respiratory irritation. Prolonged and/or repeated contact with skin may cause allergic reaction/sensitization. Deliberate concentration of vapors for purposes of inhalation is harmful and can be fatal. Harmful if swallowed. Strictly follow all use, handling and storage instructions.</li> <li>COMPONENT B: WARNING: CORROSIVE, SENSITIZER, IRRITANT. Contains amines (mixture). Contact with skin and eyes causes severe burns. Respiratory irritant. May cause eye/skin irritation. Possible skin sensitization/allergic reaction with prolonged or repeated exposure. Harmful if swallowed. Deliberate concentration of vapors for purposes of inhalation is harmful and can be fatal.</li> </ul>		





First Aid	<b>Eyes</b> – Hold eyelids apart and flush thoroughly with water for 15 minutes. <b>Skin</b> – Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. <b>Inhalation</b> – Remove to fresh air. <b>Ingestion</b> – Do not induce vomiting. Dilute with water. Contact physician. <b>In all cases, contact a physician immediately if symptoms persist.</b>		
Handling & Storage	Avoid direct contact. Wear personal protective equipment (chemical resistant goggles/gloves clothing) to prevent direct contact with skin and eyes. Use only in well ventilated areas. Open doors and windows during use. Use a properly fitted NIOSH respirator if ventilation is poor. Wash thoroughly with soap and water after use. Remove contaminated clothing and launder before reuse.		
Clean Up	Avoid contact. Wear chemical resistant clothing/gloves/goggles. In absence of adequate ventilation; use a properly fitted NIOSH respirator. Uncured material can be removed with approved solvent. Follow solvent manufacturer's instructions for use and warnings. Cured material (when Component R combined with Component H) can only be removed mechanically. In case of spill, ventilate area and contain spill. Collect with absorbent material. Dispose of in accordance with current, applicable local, state, and federal regulations.		
Additional Info	Technical Data Sheets are updated periodically. To ensure the most current version is being used, visit Technical Resources on www.sikafloorusa.com. Proper material application is the responsibility of the user. Site visits made by Sika personnel are for making technical recommendations only and not for supervising or providing quality control.		
Trouble	Problem Observed	Possible Causes	
Shooting	Peeling Between Coats	Past critical recoat time; Contamination between coats; excessive overlapping of FTP application.	
	Puddling and/or Lack of Absorption	Improper coverage rate; Insufficient profile of the slab. Stop the application, brush blast and reapply; Same issue after a brush blast indicates that the slab is too dense for the product to function as designed.	
	Slow Cure	Low floor and ambient temperatures; Use of thinner in product; Improper mixing; Product applied too thick.	
	Coating Soft	Improper mixing; Use of thinner in product; Extreme weather conditions; overapplication.	
	Cloudiness	Overapplication (product will not function as	
	(after recommended cure	designed)	
	time has passed)		

## KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY

All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikausa.com or by calling 800-933-7452.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at <u>www.sikausa.com</u> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and in-struction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical proper-ties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and as-sumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR APARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sika Mexicana S.A. de C.V.

Fracc. Industrial Balvanera

Corregidora, Queretaro

Phone: 52 442 2385800 Fax: 52 442 2250537

C.P. 76920

Carretera Libre Celaya Km. 8.5

Visit our website at www.sikafloorusa.com

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center. Sika Corporation 201 Polito Avenue Lyndhurst, NJ 07071 Phone: 800-933-7452 Fax: 201-933-6225

R

Sika Canada Inc. 601 Delmar Avenue Pointe Claire Quebec H9R 4A9 Phone: 514-697-2610 Fax: 514-694-2792

1-800-933-SIKA NATIONWIDE



