Product Data Sheet Edition 9.7.2012 Sikasil WS-290

Shefring

Sikasil[®] WS-290

SEALANT- WATERPROOFING & RESTORATION INSTITUTE Issued to: Sika Corporation Product: Sikasif WS-290 C719: Pass _____ Ext: 400% Comp:-50% Substrate: Mortar, Aluminum, Glass C661: Rating 12 Validation Date: 3/28/12 – 3/27/17 No. 312-SIK317 Copyright © 2012 SEALANT VALIDATION Www.swrionline.org

Ultra low modulus, neutral cure silicone sealant

	Sikasil WS-290 is a one-part, neutral-curing, ultra low-modulus, low to no bleed silicone sealant that cures to a durable, flexible building sealant Sikasil WS-290 performs exceptionally well under dynamic conditions due to its ultra-low modulus, high extension/compression, recovery properties and strong adhesion to most building materials. Sikasil WS-290 accommodates long-term movement of +100-50% in properly designed joints and is particularly well suited for use in Exterior Insulation Finish Systems (EIFS). Meets the requirements of ASTM C-920, Type S, Grade NS, Class 100/50, Use NT, M, G, A, O; TT-S-00230C, Type II, Class A; TT-S-001543A, Class A; CAN/CGSB-1 9.1 3-M87, AAMA 808.3			
Where to Use	 Sealing expansion and control joints in precast concrete panels and metal curtain walls. As a weatherseal in glass to glass butt joint glazing As a weatherseal in both conventional glazing and structural glazing* applications, including cap, toe and heel beads Exterior Insulation Finish Systems (EIFS) and numerous other areas requiring a high-performance seal-ant. 			
Packaging	10.0 fl.oz. (295 ml) plastic cartridges, 20 fl.oz. (600 ml) sausages			
How to Use				
Surface Preparation	The substrate must be clean, dry, frost free, sound and free of any oils, greases or incompatible sealers, paints coatings that may interfere with adhesion. POROUS SUBSTRATES – clean by mechanical methods to expose a sound surface free of contamination and laitance. NON-POROUS SUBSTRATES – for cleaning non-porous substrates, use two rag wipe method using xylene o an approved commercial solvent. Allow solvent to evaporate prior to sealant application.			
Priming	Sikasil WS-290 is designed to obtain adhesion without the use of a primer; however, certain substrates may require a primer. Test by applying the sealant and/or primer sealant combination to confirm results and proposed application methods. Refer to Technical Data Sheet for Sikasil Primer 2100 and contact Technical Service for additional information.			
	Typical Data			
	RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.			
	Shelf Life 12 months in original unopened cartridges.			
	Shelf Life	12 months in original unopened	1 cartridges	
	Shelf Life Storage Conditions	• .		
	Shelf Life Storage Conditions Colors	Store in unopened containers a	d cartridges. at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze	
	Storage Conditions	Store in unopened containers a	at temperatures lower than 80°F (27°C).	
	Storage Conditions Colors VOC Content	Store in unopened containers a White, Colonial White, Aluminu 29 g/l	at temperatures lower than 80°F (27°C).	
	Storage Conditions Colors VOC Content	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>	at temperatures lower than 80°F (27°C).	
	Storage Conditions Colors VOC Content	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or	
	Storage Conditions Colors VOC Content <u>Uncured Properties a</u> Tool Time (Initial Skin	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time)	
	Storage Conditions Colors VOC Content <u>Uncured Properties a</u> Tool Time (Initial Skin Cure Time	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days	
	Storage Conditions Colors VOC Content <u>Uncured Properties a</u> Tool Time (Initial Skin Cure Time Flow, Sag, Slump	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none	
	Storage Conditions Colors VOC Content <u>Uncured Properties a</u> Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min.	
	Storage Conditions Colors VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min.	
	Storage Conditions Colors VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>) <u>r 7 days at 77°F (25°C), 50% R</u> Capability (ASTM C-719)	30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min.	
	Storage Conditions Colors VOC Content <i>Uncured Properties a</i> Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Oynamic Movement O Elongation (ASTM D-	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)) <u>r 7 days at 77°F (25°C), 50% R</u> capability (ASTM C-719) 412)	30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min. 	
	Storage Conditions Colors VOC Content VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Cured Properties after Dynamic Movement C Elongation (ASTM D-4 Shore A Hardness (AST)	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)) <u>r 7 days at 77°F (25°C), 50% R</u> Capability (ASTM C-719) 412) STM C-661)	30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min. <i>H.</i> +100%, -50% 1200%	
	Storage Conditions Colors VOC Content VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Oynamic Movement O Elongation (ASTM D-4 Shore A Hardness (As Ozone/UV Resistance	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)) <u>r 7 days at 77°F (25°C), 50% R</u> Capability (ASTM C-719) 412) STM C-661) e (weatherometer)	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min. .H. +100%, -50% 1200% 12 Excellent	
	Storage Conditions Colors VOC Content VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Oynamic Movement O Elongation (ASTM D-4 Shore A Hardness (AS Ozone/UV Resistance Peel Strength (ASTM	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)) <u>r 7 days at 77°F (25°C), 50% R</u> capability (ASTM C-719) 412) STM C-661) e (weatherometer) C-794)	30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min.	
	Storage Conditions Colors VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Dynamic Movement O Elongation (ASTM D-4 Shore A Hardness (ASTM Ozone/UV Resistance Peel Strength (ASTM	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)	30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min.	
	Storage Conditions Colors VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Unamic Movement O Elongation (ASTM D-4 Shore A Hardness (AS Ozone/UV Resistance Peel Strength (ASTM Staining, Color Chang Staining on Porous S	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)	at temperatures lower than 80°F (27°C). m, Limestone, Black, Bronze, Medium Bronze 30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min. <i>.H.</i> +100%, -50% 120% 12 Excellent 20-40 pli none no staining	
	Storage Conditions Colors VOC Content Uncured Properties a Tool Time (Initial Skin Cure Time Flow, Sag, Slump Full Adhesion Tack Free Time Dynamic Movement O Elongation (ASTM D-4 Shore A Hardness (ASTM Ozone/UV Resistance Peel Strength (ASTM	Store in unopened containers a White, Colonial White, Aluminu 29 g/l <u>t 77°F (25°C), 50% R.H.</u>)) <u>t 77°F (25°C), 50% R.H.</u>)) Capability (ASTM C-719) t 20 C-794) (c (ASTM C-510) (c (ASTM C-1248)) (c (ASTM C-1248)) (c (ASTM C-1248))	30 minutes (higher temperatures and/or humidity will shorten this time) 7-14 days none 7-14 days 50 min.	

Application	The number of joints and the joint width should be designed for a maximum of +100 and -50% movement of joint width at time of installation. The depth of the sealant should be 1/2 the width of the joint. The maximum depth is 1/2 inch (13mm) and the minimum is 1/4 inch (6mm). To control joint depth, use closed cell polyethylene, non-gassing polyolefin or open cell polyurethane backer rod. If joint depth does not allow for backer rod, use polyethylene bond breaker tape to prevent three-sided adhesion. Closed cell backer rod should be 25% larger than joint width; do not compress more than 40%. Open cell should be compressed 40%. Do not use open cell rod in horizontal on grade joint or with E.I.F.S. When installing during time of large temperature swings such as spring or fall, and in joints designed for movement greater than ± 25 %, be aware of the significant joint movement before cure, may cause aesthetic issues such as ripples in the sealant surface. Performance will not be affected. Ready to use, apply using professional caulking gun. Do not open product container until preparation work has been completed. Apply sealant using consistent, positive pressure to force sealant into the joint. Tool sealant to create a concave joint shape and maximum adhesion. Dry tooling is recommended. DO NOT use soapy water or other liquids when tooling.
Tooling & Finishing	All joints should be masked to ensure a neat appearance and prevent sealant applied outside the joint. Place nozzle of the gun into bottom of joint and fill entire joint making complete contact with joint sides. Keep the nozzle in the sealant, continue with a steady flow of sealant preceding the nozzle to avoid air en- trapment. Tool the sealant slightly concave using dry-tooling techniques. Do not tool with soap or detergent and water solutions.
Limitations	 Do not allow sealant to come in contact with solvent during cure. Do not allow sealant to come in contact with curing polyurethane sealants during cure. Not intended for immersion. Sealant may be applied below freezing temperatures if substrates are completely dry, frost free and clean. Contact Technical Service for more information. Do not apply when substrate temperatures are below -20°F or above 130°F. Not intended for structural glazing. Not recommended for horizontal vehicular traffic. Do not apply to surfaces that will be painted as sealant surface will not hold paint. Do not apply to damp or wet substrates. Lower temperature and humidity will extend tack free and cure rates. Allow treated wood to age six months before application. Brass and copper may be discolored. Test apply prior to application. Test sensitive substrates, such as mirror backings, for compatibility before use.
CAUTION	WARNING: IRRITANT, SENSITIZER. Contains Methyl ethyl ketoxime (CAS: 96-29-7), Oximino Silane (Trade Secret). Direct eye contact may cause irritation. Eye contact may cause conjunctivitis, corneal damage, or severe chemical burns. May cause skin irritation and sensitization. May be absorbed through the skin. May cause irritation to respiratory system. May cause drowsiness. Maybe harmful if swallowed. If heated, silicones can form formaldehyde vapors. Formaldehyde is a potential cancer hazard, a known skin and respiratory sensitizer, and an irritant to the eyes, nose, throat, skin, and digestive system. Product contains oximes, possible skin sensitizers.
Handling and Storage	e Use with adequate ventilation. Product evolves Methyl ethyl ketoxime (MEKO) and methanol when exposed to water or humid air. Provide adequate ventilation to control MEKO within exposure guidelines. Keep container closed and store away from water or moisture or oxidizing materials.
First Aid	Remove to fresh air. Remove from skin and immediately flush with water for 15 minutes. Get medical attention if irritation develops or ill effects persist. Treat according to person's condition and specifics of exposure.
Clean Up	Observe personal protective equipment recommendations described in MSDS. Disposal of collected prod- uct, residues, and cleanup materials may be governmentally regulated. Observe all applicable local, state and federal waste management regulations. Wipe up and contain for disposal. Final cleaning may require use of steam, solvents, or detergents.

KEEP CONTAINER TIGHTLY CLOSED • KEEP OUT OF REACH OF CHILDREN • NOT FOR INTERNAL CONSUMPTION • FOR INDUSTRIAL USE ONLY All information provided by Sika Corporation ("Sika") concerning Sika products, including but not limited to, any recommendations and advice relating to the application and use of Sika products, is given in good faith based on Sika's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Sika's instructions. In practice, the differences in materials, substrates, storage and handling condi-tions, actual site conditions and other factors outside of Sika's control are such that Sika assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Sika product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Sika reserves the right to change the properties of its products without notice. All sales of Sika product(s) are subject to its current terms and conditions of sale which are available at www.sikausa.com or by calling 800-933-7452. Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical

Data Sheet, product label and Material Safety Data Sheet which are available online at <u>www.sikausa.com</u> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use. LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NOOTHERWARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKASHALL NOT BE LIABLE UNDERANYLEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. 1-800-933-SIKA NATIONWIDE

Visit our website at www.sikausa.com Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation 201 Polito Avenue Lyndhurst, NJ 07071 Phone: 800-933-7452 Fax: 201-933-6225

Sika Canada Inc. 601 Delmar Avenue Pointe Claire Quebec H9R 4A9 Phone: 514-697-2610 Fax: 514-694-2792

Sika Mexicana S.A. de C.V. Carretera Libre Celaya Km. 8.5 Fracc. Industrial Balvanera Corregidora, Queretaro C.P. 76920 Phone: 52 442 2385800 Fax: 52 442 2250537





Sika and Sikasil are registered trademarks Printed in Canada.